

APPROVED MATERIALS LIST

**AGGREGATES**

Aggregates from the following sources have demonstrated the capability to conform to the quality requirements of Section 1003 of the Department's Standard Specifications for Roads and Bridges, except as noted.

See 'Endnotes' and 'Notes' at the end of each section.

**A. CHERT GRAVEL AND SILICA SANDS**

Chert gravels on this list have a Friction Rating of III when used as a coarse aggregate for Asphaltic Concrete. Friction Ratings are defined in Subsection 1003.06

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 03**

**APS00006160 (A309) Dupont Sand, LLC-Carencro, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**APS00006550 (A308) L & W Sand Pit, LLC-Carencro, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**APS00007310 (A310) Vermillion Shell & Limestone Co. Inc.-Maurice, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Maurice	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**APS00011660 (A311) Perero Co. DBA-DND Landscape - Broussard, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Broussard	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**APS00011760 (A312) Lafayette Sand & Fill - Lafayette, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 03****APS00012000 Red Hawk Materials - Maurice, LA**

<b>Material</b>	<b>Approved Uses</b>
Sand Only	Granular Material for Subbase
Maurice	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00012170 Red Hawk Materials, LLC - Carencro, LA**

<b>Material</b>	<b>Approved Uses</b>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

**APS00012630 Glenn Lege Construction - Youngsville**

<b>Material</b>	<b>Approved Uses</b>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 1/12/2024	

**APS00015080 B & D Materials, LLC - Parks, LA**

<b>Material</b>	<b>Approved Uses</b>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 4/7/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**District 04****APS00006830 (A428) MRH Sand & Gravel-Benton, LA**

<b>Material</b>	<b>Approved Uses</b>
Gravel	Granular Material for Subbase
Benton	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Sand	(Friction Rating = III)
Benton	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Water Absorption = 0.5%	
Updated = 8/22/2017	

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 04**

**APS00007000 (A427) South Land Sand-Ringgold, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel Only	Base & Surface Course
Ringgold	Granular Material for Subbase
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Updated = 8/25/2017	(Friction Rating = III)
	Portland Cement Concrete

**APS00011330 (A429) Blount Brothers Construction, Inc. -Shreveport, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Blout Bros. Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

**APS00011910 Hat Creek Dirt Pit - Bossier City, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 2/17/2017	Portland Cement Concrete

**APS00012310 SiteWurx Sand - Sibley, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Sibley - 164 Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

**APS00012660 Skyplex Trucking -Bentley, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Wallace Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

**District 05**

**APS00006000 (A509) Century Ready Mix-Monroe, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Jonesboro Road	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

## A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT

## District 05

APS00007270 (A502) Martin Marietta - Perryville, LA

**Material****Approved Uses**

Gravel

Base &amp; Surface Course

Perryville

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Perryville

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00014950

Star Silica LLC. - West Monroe, LA

**Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 11/24/2021

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete - Gravel Only

APS00015510

Northeast Louisiana Sand &amp; Gravel - Willacoochee

**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 6/20/2023

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

## District 07

APS00006130 (A712) DSD Energy Services-Oakdale, LA

**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Oakdale Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00006520 (A710)

Kinder Sand Co.-Kinder, LA

**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Kinder

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 07****APS00007320 (A709) Village Sand, Inc.-Kinder, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Indian Village

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

**APS00012100****Lake Area Materials, LLC - DeRidder****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.54

Granular Material for Subbase

Water Absorption = 1.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 3/21/2017

Portland Cement Concrete

**APS00012190****Elite Sand - Longville, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 4/13/2017

Portland Cement Concrete

**APS00012390****Gator Aggregates - Deridder, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Pippin Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pippin Pit

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

**APS00014360****Arcosa Aggregates - Anacoco Plant 1391-Merryville****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absorption = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/3/2022

Portland Cement Concrete

## A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT

## District 07

## APS00014370 Arcosa Aggregates - Indian Village Plant 1284

**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 7/29/2022

Portland Cement Concrete

## APS00014470 Merryville Aggregate, LLC - Evans, LA

**Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.56

Granular Material for Subbase

Water Absorption = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 2/12/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

## APS00014890 Longville Sand and Gravel - Longville, LA

**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 10/5/2021

## APS00014960 Arcosa Aggregates - West Merryville, LA

**Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 7/17/2023

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete

## APS00015140 Arcosa Aggregates - Plant LA 1343 - DeRidder

**Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.57

Granular Material for Subbase

Water Absorption = 0.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 5/4/2022

Portland Cement Concrete

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 08****APS00007150 (A844) Tanner Heavy Equipment Co-Leesville, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Tanner Pit #2

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/25/2017

**APS00007300 (A822) Martin Marietta - Woodworth, LA****Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

(Friction Rating = III)

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

(Gravel from this source contains an unusual amount of hematite iron ore, if used in Portland Cement Concrete, the hematite content cannot exceed 2%)

**APS00011680 (A847) Larry Grayson & Son Trucking, LLC -Forest Hill, LA****Material****Approved Uses**

Gravel

Granular Material for Subbase

Ahtus Melder Rd Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.57

Asphaltic Surface Treatment

Water Absorption = 1.0%

Asphaltic Concrete

Sand

(Friction Rating = III)

Ahtus Melder Rd Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/22/2017

**APS00011710 (A849) Diamond B Construction Co.,LLC - Boyce, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Hot Wells / Gardener Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

**APS00011720 (A850) Diamond B Construction Co., LLC Woodworth, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Woodworth Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 08**

**APS00014440 Cenla Materials - Forest Hill, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.55	Granular Material for Subbase
Water Absportion = 1.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III)
Updated = 8/25/2020	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**District 58**

**APS00007130 (A914) Swim Enterprises-Columbia, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Columbia	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/22/2017	

**APS00007290 (A913) Martin Marietta - Jena, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Jena	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Jena	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/22/2017	

**APS00011810 (A916) Amberg Construction - Olla, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Aimwell	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Aimwell	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	
Updated = 8/22/2017	



**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 58**

**APS00015030 Amberg Construction, LLC. - Jena**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absorption = 1.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 4/7/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00015090 D & J Construction Co., LLC - Aimwell, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 4/7/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**District 61**

**APS00002200 (A628) Bear Industries - Port Allen, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Port Allen	
Spec. Gravity-SSD = 2.62	
Water Absorption = 0.5%	
Updated = 8/22/2017	

**APS00005950 (A646) Bunch Sand and Gravel #1 - Clinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pit #1	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absorption = 1.3%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pit #1	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	
Updated = 7/26/2018	

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 61**

**APS00006180 (A636) Feliciana Farms, Inc.-St. Francisville, LA**

**Material**

**Approved Uses**

Gravel		Base & Surface Course
Bayou Sara		Granular Material for Subbase
Spec. Gravity-SSD = 2.54		Special Embankment (non-plastic)
Water Absorption = 1.7%		Asphaltic Surface Treatment
Sand		Asphaltic Concrete
Bayou Sara		(Friction Rating = III)
Spec. Gravity-SSD = 2.62		Portland Cement Concrete
Water Absorption = 0.5%		

Updated = 8/22/2017

**APS00006400 (A632) Hooper Road Dirt Pit-Baton Rouge, LA**

**Material**

**Approved Uses**

Sand Only		Granular Material for Subbase
Baton Rouge		Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62		Asphaltic Concrete
Water Absorption = 0.5%		Portland Cement Concrete

Updated = 8/22/2017

**APS00007010 (A640) Southern Aggregates, LLC-Norwood, LA**

**Material**

**Approved Uses**

Gravel		Base & Surface Course
Felps		Granular Material for Subbase
Spec. Gravity-SSD = 2.53		Special Embankment (non-plastic)
Water Absorption = 2.2%		Asphaltic Surface Treatment
Sand		Asphaltic Concrete
Felps		(Friction Rating = III)
Spec. Gravity-SSD = 2.62		Portland Cement Concrete
Water Absorption = 0.5%		

Updated = 8/22/2017

**APS00011640 (A644) Fleniken Sand & Gravel Inc - Clinton, LA**

**Material**

**Approved Uses**

Gravel		Granular Material for Subbase
Acme Pit		Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52		Asphaltic Surface Treatment
Water Absorption = 1.9%		Asphaltic Concrete
Sand		(Friction Rating = III)
Acme Pit		Portland Cement Concrete
Spec. Gravity-SSD = 2.62		
Water Absorption = 0.5%		

Updated = 7/26/2018

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 61**

**APS00011650 (A645) Dolese Bros-St.HelenaSand&Gravel - Pine Grove, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
St. Helena S&G Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.6%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
St. Helena S&G Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 6/3/2020

**APS00011920 Regional Sand & Gravel - Clinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Highway 960 Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Highway 960 Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

**APS00012530 Dennis Stewart Equipment Rental,Inc Baton Rouge,LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Joor Road Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

**APS00012910 South Louisiana Fill Materials, LLC - Darrow, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 1/5/2024

**APS00014150 Lionel Boudreaux Trucking, LLC - St. Francisville**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 10/16/2019	Portland Cement Concrete

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 61**

**APS00014180 Ivey Enterprises, LLC - Greenwell Springs, LA**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 2.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 10/16/2019

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00014850 Superior Sand & Gravel - Plant 1 - Clinton, LA**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.57

Granular Material for Subbase

Water Absorption = 0.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 10/5/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00014860 Superior Sand & Gravel - Plant 2 - Clinton**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 10/5/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00015000 Barriere Construction Co. LLC - Map Pit**

**Material**

**Approved Uses**

Sand Only

Base & Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 3/28/2022

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete - Gravel Only

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 61****APS00015150 Arcosa Aggregates - Plant LA 1342 - Clinton Pit****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/3/2022

Portland Cement Concrete

**APS00015490****South Louisiana Fill Materials LLC - Convent****Material****Approved Uses**

Sand Only

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 1/5/2024

**APS00015520****Superior Sand & Gravel - Plant 3 - Greenwell Sprgs****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 9/19/2023

Asphaltic Surface Treatment

Asphaltic Concrete

Portland Cement Concrete - Gravel Only

**District 62****APS00005700 (AX04) Accardo Materials, Inc-Franklinton,LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Isabel

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Isabel

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

**APS00005870 (AY06) Bass Sand & Gravel-Bogalusa, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Bogalusa

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Bogalusa

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00005990 (AY10) Cash Sand & Gravel, Inc.-Denham Springs, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Easterly Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Easterly Plant

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 7/26/2018

**APS00006060****Crawford Aggregate Industr-Pine Grove,LA - Jenkins****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Jenkins Lane

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Jenkins Lane

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 6/3/2020

**APS00006100 (AX71)****Daley Sand & Gravel-Roseland,LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Roseland

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 3.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Roseland

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006170 (AY17)****Brownstone Sand & Gravel - Franklinton, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Enon Plant - Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Enon Plant - Franklinton

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete - Gravel Only

Water Absorption = 0.5%

Updated = 10/26/2021

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00006190 (AY24) Florida Parishes Aggregate-Fluker, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Kent Pit - Fluker

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Kent Pit - Fluker

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006240 (AX91) Gillman Enterprises, LLC-Independence, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Independence

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Independence

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006350 (AY14) Hard Rock Sand & Gravel LLC - Franklinton, LA - #2****Material****Approved Uses**

Gravel

Base &amp; Surface Course

#2 - Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

#2 - Franklinton

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006360 (AX89) Hard Rock Sand & Gravel, LLC-Mt. Hermon, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Mt. Hermon

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Mt. Hermon

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00006450 (AX72) Industrial Aggregates, LLC-Franklinton, LA-Pine CI****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete

**APS00006510 (AX68) K & C Gravel-Independence,LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

**APS00006590 (AY03) Lafarge - Holcim Aggregates -Honey Island****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Honey Island

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Surface Treatment

Water Absorption = 0.5%

Asphaltic Concrete

Honey Island

(Friction Rating = III)

Updated = 9/20/2023

Portland Cement Concrete

**APS00006600 (AY01) Lafarge Aggregates-Bogalusa,LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Isabel

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Isabel

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006670 (AX43) Lon Land Gravel Co.-Mt Hermon, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Franklinton

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017



**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 62**

**APS00006770 (A135) Mears Sand & Gravel-Denham Springs,LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Dennis Mills	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absportion = 2.0%	Asphaltic Concrete
Sand	(Friction Rating = III)
Dennis Mills	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Water Absportion = 0.5%	

Updated = 6/3/2020

**APS00006850 (AY12) P & J Sand & Gravel, LLC-Independence, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Independence	Granular Material for Subbase
Spec. Gravity-SSD = 2.48	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Independence	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

**APS00006920 (AX29) Ram Industries-Mt. Hermon, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklinton	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017 (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00006990 (AX69) Smith Sand & Gravel-Franklinton,LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklinton	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 62**

**APS00007030 (AY26) Southern Aggregates, LLC-DenhamSprings,LA-Plant7**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Plant #7	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 1.8%	Asphaltic Concrete
Sand	(Friction Rating = III)
Plant #7	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 7/26/2018

**APS00007140 (AX96) T & D Sand & Gravel, LLC-Independence, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Amite	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Amite	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

**APS00007490 (AB98) Willis Sand & Gravel-Bogalusa, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Sun	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 2.5%	Asphaltic Concrete
Sand	(Friction Rating = III)
Sun	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 8/24/2017

**APS00011340 (AY29) BMS, LLC - Amite, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Amite Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Amite Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00011410 (AX75) Hard Rock Sand & Gravel LLC - Franklinton, LA - #1**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
#1 Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.51	Special Embankment (non-plastic)
Water Absorption = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#1 Franklinton	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00011460 (AY30) Hunt Gravel - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.51	Special Embankment (non-plastic)
Water Absorption = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklinton	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	
Updated = 8/24/2017	

**APS00011520 (AY31) Industrial Mining Plant 5 - Tickfaw, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Black Cat Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absorption = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Black Cat Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	
Updated = 8/25/2017	

**APS00011700 (AY34) Madden Roseland, LA Gravel Pit - Roseland, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Formerly Diamond B	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absorption = 2.1%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Formerly Diamond B	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
Formerly Diamond B	
Updated = 1/26/2023	

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 62**

**APS00011790 (AY32) Southern Aggregates - Amite, LA - #9**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Plant #9	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absorption = 2.3%	Asphaltic Concrete
Sand	(Friction Rating = III)
Plant #9	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absorption = 0.5%	

Updated = 8/6/2018

**APS00011800 (AY33) Bunch's Sand and Gravel #2 - Greensburg, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Pit #2	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 1.8%	Asphaltic Concrete
Sand	(Friction Rating = III)
Pit #2	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absorption = 0.5%	

Updated = 7/26/2018

**APS00011940 Baldwin Redi-Mix Co. Inc.-Greensburg,H&LIsland Pit**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absorption = 1.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)

Updated = 7/26/2018

**APS00012340 River Road Rock - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Mt. Hermon Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absorption = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Mt. Hermon Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 62**

**APS00012420 Tate Construction, LLC - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Tate Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absorption = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Tate Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

**APS00012510 Industrial Aggregates, LLC - Covington, LA - #2**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Enon Plant #2	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absorption = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Enon Plant #2	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

**APS00012620 Industrial Aggregates - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pine Cliff Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absorption = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pine Cliff Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

**APS00013080 Northern Sand & Gravel, L.L.C. - Independence**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absorption = 2.4%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)

Updated = 4/29/2020

Portland Cement Concrete

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00013250****R & S Dozer Service, LLC - Franklinton****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 10/22/2021

Portland Cement Concrete - Gravel Only

**APS00013390****L & C Gravel, LLC - Plant #6 - Fluker****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.9%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 9/12/2019

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00014300****Southern Aggregates, LLC Plant 31 - Franklinton****Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

(Friction Rating = III)

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 7/16/2020

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00014350****Barriere Construction Co., LLC - Independence, LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 7/15/2020

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00014410 Arcosa Aggregates - Pearl River Plant 1725****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 3.3%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/3/2022

Portland Cement Concrete

**APS00014780****Cash Sand & Gravel, Inc. - Kemp Plant -D.S., LA****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 10/5/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00014990****Barriere Construction Co. LLC - Miley Pit****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 2/22/2022

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00015160****Arcosa Aggregates - Plant LA 1349 - Pearl River****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 3.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 5/4/2022

Portland Cement Concrete

**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**

**District 62**

**APS00015170 Arcosa Aggregates - Plant LA 1341 - Independence**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absportion = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III)

Updated = 5/4/2022

Portland Cement Concrete

**APS00015200 Arcosa Aggregates - Plant LA 1345 - Franklinton**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absportion = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III)

Updated = 5/4/2022

Portland Cement Concrete

**APS00015210 Arcosa Aggregates - Plant LA 1340 - Denham Springs**

**Material**

**Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absportion = 2.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III)

Updated = 5/4/2022

Portland Cement Concrete

**APS00015410 Crawford Aggregate Industries - Cross Pit**

**Material**

**Approved Uses**

Sand Only

Base & Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absportion = 0.5%

Special Embankment (non-plastic)

Updated = 5/23/2023

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)



**A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT****District 62****APS00015460 Louisiana Aggregate Materials, LLC-DenhamSprings****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 12/22/2023

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00015650 Accardo Mining, LLC. - Bogalusa****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 10/9/2023

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete - Gravel Only

**APS00015670 Candies Excavation, Inc. - Folsom****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 1/12/2024

**APS00015680 A-1 Aggregates - KSB Holdings, LLC - Mt. Hermon****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Spec. Gravity-SSD = 2.62

Granular Material for Subbase

Water Absorption = 0.5%

Special Embankment (non-plastic)

Updated = 1/12/2024

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete - Gravel Only

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

## Out of State

**APS00005730 (ASAN) Alabama Sand and Gravel-Prattville, AL****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Billingsley Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.63

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Billingsley Pit

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00005740 (ASAV) Alliance Sand and Gravel, LLC-Phil Campbell, AL****Material****Approved Uses**

Sand Only

Special Embankment (non-plastic)

Phil Campbell Pit

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00005750 (ASAK) Allstate Deatsville, LLC-Deatsville, AL****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Deatsville Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

**APS00005780 (ABAO) Arkansas Gravel Company, Inc.-Hampton, AR****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Bradshaw Mine

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Bradshaw Mine

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00005790 (AB76) B & B Gravel & Trucking Co.-Bearden, AR****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absorption = 1.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS****Out of State****APS00005830 (ASAR) Baldwin Sand & Gravel-Crystal Springs,MS**

<b>Material</b>	<b>Approved Uses</b>
Gravel	Base & Surface Course
Crystal Springs Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.57	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Crystal Springs Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00005920 (ASAM) Blackwell Aggregates, Inc.-Nicholson, MS**

<b>Material</b>	<b>Approved Uses</b>
Gravel	Base & Surface Course
Jackson Landing Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.48	Special Embankment (non-plastic)
Water Absorption = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Jackson Landing Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	
Updated = 8/24/2017	

**APS00005930 (AB31) Blain Sand & Gravel, Inc.-Natchez, MS**

<b>Material</b>	<b>Approved Uses</b>
Gravel	Granular Material for Subbase
Coverhill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.57	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Sand	(Friction Rating = III)
Coverhill Pit	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Water Absorption = 0.5%	
Updated = 8/24/2017	

**APS00005940 (AA57) Blain Sand & Gravel, Inc.-Crystal Springs, MS**

<b>Material</b>	<b>Approved Uses</b>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absorption = 1.7%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 8/24/2017	Portland Cement Concrete

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

**Out of State**

**APS00006030 Cossatot Rock, LLC-Lockesburg, AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Old Deirks Hwy Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Old Deirks Hwy Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.59	Portland Cement Concrete
Water Absportion = 1.0%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00006110 (AA80) Dickerson & Bowen Riverside Gravel-Tylertown, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
McComb	Granular Material for Subbase
Spec. Gravity-SSD = 2.46	Special Embankment (non-plastic)
Water Absportion = 4.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
McComb	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	
Updated = 8/24/2017	

**APS00006200 (ASAT) Foley Materials Co.-Phenix City, AL- Plant 501**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Plant 501	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/24/2017	

**APS00006210 (ASAJ) Foley Materials Co.-Phenix City, AL- Plant 505**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Plant 505	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete
Updated = 8/24/2017	

**APS00006230 (ASAI) Fouke Sand & Gravel, LLC-Fouke, AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.61	Granular Material for Subbase
Water Absportion = 0.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III)
Updated = 8/24/2017	Portland Cement Concrete

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

**Out of State**

**APS00006260 (ABAK) Green Brothers Gravel Co.-Hazlehurst, MS**

**Material**

**Approved Uses**

Gravel	Base & Surface Course
#22	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absorption = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#22	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

**APS00006270 (ABAL) Green Brothers Gravel Co.-CrystalSprings, MS**

**Material**

**Approved Uses**

Gravel	Base & Surface Course
#65	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absorption = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#65	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

**APS00006290 (ASAW) Hallet Materials-Porter, TX**

**Material**

**Approved Uses**

Sand Only	Granular Material for Subbase
Porter Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

**APS00006300 (ASAU) Hammett Gravel Company, Inc.-Benton, MS**

**Material**

**Approved Uses**

Gravel	Base & Surface Course
Yazoo City Operation	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absorption = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Yazoo City Operation	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

## Out of State

**APS00006310 (AA70) Hanson Aggregates-Bearden,AR****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Eagle Mills

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Eagle Mills

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

**APS00006320 (A092) Heidelberg Materials - Little River Plant****Material****Approved Uses**

Sand Only

Base &amp; Surface Course

Little River F.K.A. Hanson

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Surface Treatment

Little River F.K.A. Hanson

Asphaltic Concrete

Updated = 5/22/2023

(Friction Rating = III)

Portland Cement Concrete

**APS00006420 (AB07) Huey Stockstill, LLC - Picayune, MS - 12 Oaks****Material****Approved Uses**

Gravel

Base &amp; Surface Course

12 Oaks Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

12 Oaks Pit

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

**APS00006430 (AB26) Huey P. Stockstill, LLC -Picayune, MS - Pine Grove****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Pine Grove Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pine Grove Pit

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

**Out of State**

**APS00006490 (ABAP) JJ Ferguson Sand & Gravel-Cruger, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Blackhawk Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absorption = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Blackhawk Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

**APS00006500 (A091) Johnsville Sand & Gravel-Hermitage, AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absorption = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	(Friction Rating = III)
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

**APS00006530 (ASAG) King Sand & Gravel-Kerens, TX**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete

**APS00006540 (AB91) Krystal Gravel, Inc.-Crystal Springs, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absorption = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 8/24/2017	Portland Cement Concrete

**APS00006680 (ASAL) Marion Clay & Gravel, LLC-Columbia, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absorption = 3.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 8/24/2017	Portland Cement Concrete

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

## Out of State

**APS00006700 (ABAS) Martin Marietta Aggregates-Eagletown, OK****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Broken Bow Sand &amp; Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Asphaltic Surface Treatment

Water Absorption = 1.2%

Asphaltic Concrete

Sand

(Friction Rating = III)

Broken Bow Sand &amp; Gravel

Portland Cement Concrete - Gravel Only

Spec. Gravity-SSD = 2.74

Water Absorption = 0.4%

Broken Bow Sand &amp; Gravel

Updated = 7/18/2023

**APS00006720 (ASAX) Martin Marietta Aggregates-Garwood, TX****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Garwood Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Garwood Plant

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete

**APS00006780 (ABAC) Memphis Stone & Gravel Co.-Nesbit, MS****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Anderson Plant

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

**APS00006790 (ABAD) Memphis Stone & Gravel Co.-Senatobia, MS****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Perry Plant

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

**APS00006840 (ASAQ) ODDEE Smith Constr.Inc.-Brookhaven, MS****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Oddee California Camp Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Oddee California Camp Pit

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete



**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

## Out of State

**APS00006860 (A018) Perkinston Sand & Gravel-Perkinston, MS****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

**APS00006910 (ASAF) R & R Logging & Gravel-Columbia, MS****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 3.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete

**APS00006930 (ASAP) Riverside Sand & Gravel-Tylertown, MS****Material****Approved Uses**

Sand Only

Granular Material for Subbase

NW St. Paul Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

**APS00006980 (ASAY) Simpson Materials Co.-Valley Park, MO****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Ranken Site

Granular Material for Subbase

Spec. Gravity-SSD = 2.51

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Ranken Site

(Friction Rating = III)

Updated = 8/28/2017

Portland Cement Concrete

**APS00007170 (AB27) The Fordyce Co-Victoria, TX****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Briggs Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.74

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Briggs Plant

(Friction Rating = III)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/28/2017

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

## Out of State

**APS00007210 (ASAH) Triangle Aggregates, LLC-Jackson, AL****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Couch - Triangle Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.61

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Couch - Triangle Pit

(Friction Rating = III)

Spec. Gravity-SSD = 2.63

Portland Cement Concrete

Updated = 8/28/2017

**APS00007250 (ASAE) Trinity Materials-West Lockesburg, AR****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.56

Granular Material for Subbase

Water Absorption = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/28/2017

Portland Cement Concrete

**APS00007510 (ASAA) Wooten Sand & Gravel-Fouke,AR****Material****Approved Uses**

Gravel

Base &amp; Surface Course

Spec. Gravity-SSD = 2.60

Granular Material for Subbase

Water Absorption = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III)

Updated = 8/24/2017

Portland Cement Concrete

**APS00011350 (ASAS) Eastern Oklahoma Quarries, LLC - Spiro, OK****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spiro Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

**APS00011360 (ASAZ) Shale Support Holdings, LLC - Nicholson, MS****Material****Approved Uses**

Gravel

Granular Material for Subbase

Nicholson Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.49

Asphaltic Surface Treatment

Water Absorption = 3.5%

Asphaltic Concrete

Sand

(Friction Rating = III)

Nicholson Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.63

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/28/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

Out of State

**APS00011380 (ASBA) South Gate Aggregates, LLC - Nicholson, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Burge Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Burge Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.63	Portland Cement Concrete
Updated = 8/28/2017	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00011450 (ASBC) Huey P. Stockstill, LLC- Nicholson, MS**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Santa Rosa Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00011470 (ASBB) Eastern Oklahoma Quarries - Garland, AR**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Chieftan Sand Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Water Absportion = 0.8%	Portland Cement Concrete
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00011630 (ASBE) Heidelberg Materials - Bristol Plant**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Bristol Plant F.K.A. Hanson	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Portland Cement Concrete
Updated = 5/22/2023	

**APS00011690 (ASBF) Hammatt & Green Aggregates - Vicksburg, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Henry Mine Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Henry Mine Pit	(Friction Rating = III)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	
Updated = 1/8/2019	

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

**Out of State**

**APS00012160 Dickerson & Bowen Co., Inc - Brookhaven, MS**

**Material**

**Approved Uses**

Gravel Only	Base & Surface Course
D & B Brookhaven Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.2%	Asphaltic Concrete
Updated = 8/28/2017	(Friction Rating = III)
	Portland Cement Concrete

**APS00012380 LeHigh Hanson - Garwood, TX**

**Material**

**Approved Uses**

Sand Only	Granular Material for Subbase
Arena Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete
Updated = 8/24/2017	

**APS00012890 D & J Construction Company, LLC - West Monroe**

**Material**

**Approved Uses**

Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 1/16/2018	Portland Cement Concrete

**APS00012930 Regional Sand & Gravel, LLC #2 - Clinton**

**Material**

**Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absorption = 1.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 7/26/2018	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00012980 Gulf Coast Sand & Gravel - Jackson, AL**

**Material**

**Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.59	Granular Material for Subbase
Water Absorption = 1.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Updated = 1/16/2018	(Friction Rating = III)
	Portland Cement Concrete

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

**Out of State**

**APS00013340 Heritage Sand and Gravel - Columbia, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absorption = 3.0%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III)
Updated = 4/7/2020	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

**APS00014030 Sierra FRAC Sand - Plain Dealing**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 11/15/2018	Portland Cement Concrete

**APS00014570 Arkansas Granufill Supply - Hot Springs, AR**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Spec. Gravity-SSD = 2.59	Supplemental Fines (screenings) for Asphaltic Concrete
Water Absorption = 1.5%	
Updated = 10/5/2021	

**APS00014750 Rock Island Sand and Gravel - Harrell Pit-Hampton**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.58	Granular Material for Subbase
Water Absorption = 1.0%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 1.0%	(Friction Rating = III)
Updated = 10/5/2021	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00014970 Gulf Coast Sand - Nicholson, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absorption = 2.9%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.68	Asphaltic Concrete
Water Absorption = 0.1%	(Friction Rating = III)
Updated = 1/27/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

## A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS

## Out of State

## APS00015010 Island Sand &amp; Gravel - Crossett, AR

**Material**

Sand Only

Spec. Gravity-SSD = 2.64

Water Absorption = 0.2%

Updated = 3/28/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete - Gravel Only

## APS00015130

## Lafarge Aggs - Cave-In-Rock, IL - Transition Ledge

**Material**

Sand

Stone

(Limestone)

Spec. Gravity-SSD = 2.65

Water Absorption = 1.3%

Updated = 6/20/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV)

Riprap &amp; Stone Revetment

## APS00015180

## Arcosa Aggregates - Plant 1347 - Hattiesburg, MS

**Material**

Gravel

Spec. Gravity-SSD = 2.53

Water Absorption = 2.2%

Sand

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 5/4/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete

## APS00015190

## Arcosa Aggregates - Plant 1348 - Columbia, MS

**Material**

Gravel

Spec. Gravity-SSD = 2.53

Water Absorption = 2.2%

Sand

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 5/4/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = III)

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

## APS00015310

## Hastie Mining and Trucking #2 - Cave-In-Rock, IL

**Material**

Sand

Stone

(Siliceous Limestone)

Spec. Gravity-SSD = 2.69

Water Absorption = 1.0%

Updated = 7/29/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV)

Riprap &amp; Stone Revetment

**A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**

Out of State

**APS00015540 Hammett Gravel Company, Inc. - Red Mountain Plant**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Base & Surface Course
Spec. Gravity-SSD = 2.64	Granular Material for Subbase
Water Absorption = 0.5%	Special Embankment (non-plastic)
Updated = 9/19/2023	Asphaltic Surface Treatment
	Asphaltic Concrete
	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

**APS00015780 RockCo Mining, LLC. - Courtland, MS**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Base & Surface Course
Spec. Gravity-SSD = 2.65	Granular Material for Subbase
Water Absorption = 0.4%	Special Embankment (non-plastic)
Updated = 1/12/2024	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete - Gravel Only

**NOTES:**

**Note A-1:**

Source approval samples of gravel and sand are obtained by personnel of the Materials and District Laboratories. The source is defined as the pit or quarry which produces the aggregate being evaluated. All aggregate which does not pass through the 4.75mm (No. 4) sieve shall be source approved prior to use. Certain aggregates may be approved for restricted use. A complete source approval analysis shall be run on each aggregate source.

**Note A-2:**

All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

**Note A-3:**

A specific gravity value of 2.62 (SSD) may be used for all in-state silica sands used for portland cement concrete.

**Note A-4:**

Because absorption has been found to correlate with the type and specific gravity of silica sands and chert gravels, the water absorption factors given in the following table may be used:

**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00005710 (ABBC) Agrecasa Del Caribe-San Pedro Sula, HON****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.63	Special Embankment (non-plastic)
Water Absorption = 1.6%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00005770 (ABBY) APAC - Brickey's Stone-Bloomsdale, MO - Burlington****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Burlington Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absorption = 1.4%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = III)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00005900 (AB25) Arcosa Lightweight - Erwinville, LA****Material****Approved Uses**

Lightweight Aggregate	Special Embankment (non-plastic)
(Expanded Clay)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 1.65	(Type B, C, & D applications only)
Water Absorption = 16.3%	Asphaltic Concrete
Updated = 12/8/2021	(excluding wearing surfaces)
	(Friction Rating = I)
	Portland Cement Concrete

**APS00005960 (ABBU) Winn Materials of Kentucky-Grand Rivers,KY-StLouis****Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
St. Louis Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 10/20/2021	(Friction Rating = IV)
	Riprap & Stone Revetment



**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00005970 (ABBK) Texas Materials - Burnet.TX**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
F.K.A OldCastle Materials -	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 1/12/2024	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00006080 (ABBN) Crystal Hill Quarry-North Little Rock, AR**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Granite Mountain Quarries	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 8/24/2017	(Friction Rating = II)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00006120 (AB28) 3M Industrial Minerals Prods Div. - Little Rock,AR**

<u>Material</u>	<u>Approved Uses</u>
Granite	Base & Surface Course
Syenite Granite Fines-Manf.Snd	Granular Material for Subbase
Spec. Gravity-SSD = 2.63	Special Embankment (non-plastic)
Water Absorption = 0.2%	Asphaltic Surface Treatment
Updated = 8/28/2017	Asphaltic Concrete
	Supplemental Fines (screenings) for Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00006250 (A033) Granite Mountain Quarries-Little Rock, AR**

<u>Material</u>	<u>Approved Uses</u>
Granite	Base & Surface Course
Syenite Granite	Granular Material for Subbase
Spec. Gravity-SSD = 2.59	Special Embankment (non-plastic)
Water Absorption = 0.9%	Asphaltic Surface Treatment
Updated = 8/24/2017	Asphaltic Concrete
	(Friction Rating = II)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

Out of State

**APS00006340 (A077) Hanson Aggregates-Perch Hill Plant-Chico,TX**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Perch Hill Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00006370 (AA90) Hastie Mining Company-Cave-in-Rock,IL**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Hastie Mining Company Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 8/24/2017	(Friction Rating = I)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00006440 (AA91) Ideal Domicana, SA-Santo Domingo, DR**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.61	Special Embankment (non-plastic)
Water Absorption = 1.3%	Asphaltic Surface Treatment
Updated = 8/25/2017	Portland Cement Concrete

**APS00006480 (ABBO) Jamaica Aggregates Limited dba Lafarge**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Crushed Alluvial Stone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.72	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

**APS00006560 (ABAN) Lafarge Aggregates-Cave-In-Rock, IL - SandStone**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 0.8%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = I)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

**Out of State**

**APS00006570 (ABAM) Lafarge Aggregates-Cave-In-Rock, IL - Sil. Limestn**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Ledge 8 - 10	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = III)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00006580 (ABCA) Lafarge Aggregates-Fredonia, KY**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

**APS00006690 (AA86) Martin Marietta Aggregates-Bahamas,BAH**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Porous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absorption = 3.9%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**Out of State**

**APS00006710 (AA92) Martin Marietta Aggregates-Cove,AR**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Rhyolite)	Granular Material for Subbase
Traprock	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 7/20/2022	(Friction Rating = II)
	Riprap & Stone Revetment

**APS00006730 (ABAW) Martin Marietta Aggregates-Malvern, AR - SandStone**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Jones Mill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.2%	Asphaltic Concrete
Updated = 8/25/2017	(Friction Rating = II)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00006740 (ABAX) Martin Marietta Aggregates-Malvern, AR - Granite**

**Material**

**Approved Uses**

Granite	Base & Surface Course
Jones Mill Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.58	Special Embankment (non-plastic)
Water Absorption = 0.9%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS****APS00006750 (AA39) Martin Marietta Aggregates-Mulgrave, NS**

<u>Material</u>	<u>Approved Uses</u>
Granite	Base & Surface Course
Spec. Gravity-SSD = 2.70	Granular Material for Subbase
Water Absorption = 0.9%	Special Embankment (non-plastic)
Updated = 6/3/2020	Asphaltic Surface Treatment
	Asphaltic Concrete
	(excluding OGFC and coarse mix)
	(Friction Rating = I)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

**APS00006760 (AA51) Martin Marietta Aggregates-Sawyer,OK**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absorption = 2.3%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = I)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

**APS00006880 (AB13) Pine Bluff Sand & Gravel-Deleware, AR**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
River Mountain Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Updated = 11/10/2020	(Friction Rating = I)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

**APS00006890 (ABBS) Pine Bluff Sand & Gravel-Salem,KY**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Cumberland River Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 10/28/2021	(Friction Rating = III)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

**APS00007160 (AB15) Texas Crushed Stone Co., Inc.-Georgetown, TX**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.48	Special Embankment (non-plastic)
Water Absorption = 3.6%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00007180 (A056) Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn8**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.64	Special Embankment (non-plastic)
Water Absorption = 1.6%	Asphaltic Surface Treatment
Updated = 5/21/2018	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00007190 (A079) Tower Rock Stone Co-St.Genevieve, MO- Oolitic**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Oolitic Stone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absorption = 4.8%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**Out of State**

**APS00007260 (AB61) Martin Marietta - Bridgeport TX**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Bridgeport	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absorption = 1.3%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

## APS00007340 (A042) Vulcan Materials Co-Calera, AL

**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Calera Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.71	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

## APS00007350 (AA95) Vulcan Materials Co-Cancun, MEX

**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absorption = 3.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

## APS00007380 (ABBQ) Vulcan Materials Co-Grand Rivers,KY- Ft Payne

**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Ft. Payne Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.2%	Asphaltic Concrete
Updated = 10/29/2021	(Friction Rating = III)
	(Friction Rating = II for ADT <= 20,000)

## APS00007390 (ABBP) Vulcan Materials Co-Grand Rivers,KY- Warsaw

**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 10/29/2021	(Friction Rating = IV)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00007430 (ABBT) Vulcan Materials Co-Tuscumbia, AL- Pride Quarry**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.60	Special Embankment (non-plastic)
Water Absorption = 1.9%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00007450 (AB19) Vulcan Materials Co-Trinity, AL**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Trinity Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.2%	Asphaltic Concrete
Updated = 10/25/2017	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00007480 (ABAY) Warren Paving-Salem, KY-Slats Lucas Quarry**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Slats Lucas Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absorption = 0.4%	Asphaltic Concrete
Updated = 10/20/2021	(Friction Rating = III)
	(Friction Rating = II for ADT <10,000)
	Riprap & Stone Revetment

**APS00007500 (AB78) Winn Materials, Inc.-Clarksville, TN**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absorption = 0.6%	Asphaltic Surface Treatment
Updated = 10/28/2021	Asphaltic Concrete
	(Friction Rating = IV)
	Riprap & Stone Revetment



**B. OTHER AGGREGATE MATERIALS**

**APS00007520 (AB04) Delta Materials - Marble Falls, TX**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absorption = 2.1%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = I)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00011430 (ABCD) APAC - Brickey's Stone-Bloomsdale, MO - Plattin**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Plattin Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 7/26/2018	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00011620 (ABCI) Central Stone Co - Farmington, MO**

**Material**

**Approved Uses**

Granite	Base & Surface Course
Butler Hill Granite Quarry	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.3%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00011870 Lafarge Aggregates-Smithland, KY-Three Rivers-S1**

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
3RvrQry-Bench S1-Pit#1	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Updated = 5/20/2020	(Friction Rating = III)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS****APS00012130 Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn12****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Ledge 12	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 11/9/2018	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00012300 Vulcan Materials Co-West Loachapoka, AL****Material****Approved Uses**

Granite	Base & Surface Course
Spec. Gravity-SSD = 2.62	Granular Material for Subbase
Water Absorption = 0.4%	Special Embankment (non-plastic)
Updated = 8/25/2017	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

**APS00012320 Winn Materials of Kentucky-Grand Rivers,KY-Warsaw****Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.1%	Asphaltic Concrete
Updated = 11/10/2020	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00012600 Martin Marietta - MMR - Hondo, TX****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Medina Rock & Rail Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.2%	Asphaltic Concrete
Updated = 8/29/2017	(Friction Rating = IV)
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00012680 Warren Paving-Salem, KY-Lower Warsaw Formation****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Lower Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**APS00012880 Lafarge Aggregates-Smithland, KY-Three Rivers-S2****Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absorption = 0.8%	Asphaltic Surface Treatment
Updated = 5/20/2020	Asphaltic Concrete
	(excluding OGFC and coarse mix)
	(Friction Rating = III)
	Riprap & Stone Revetment

**APS00012960 R4 ObrusS.A. D.C.V. - Boca Del Rio, Mexico****Material****Approved Uses**

Granite	Base & Surface Course
Spec. Gravity-SSD = 2.89	Granular Material for Subbase
Water Absorption = 1.5%	Special Embankment (non-plastic)
Updated = 1/16/2018	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00014110 Rogers Group - Lacey's Springs Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Surface Treatment
Updated = 2/14/2020	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS****APS00014340 Lafarge Aggregates-Smithland, KY-Upper Fredonia****Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 10/21/2020	Asphaltic Concrete
	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00014530 Martin Marietta - Mill Creek - Granite****Material****Approved Uses**

Granite	Base & Surface Course
Spec. Gravity-SSD = 2.74	Granular Material for Subbase
Water Absorption = 1.0%	Special Embankment (non-plastic)
Updated = 1/26/2021	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**Out of State****APS00014540 Martin Marietta - Mill Creek - Limestone****Material****Approved Uses**

Stone	Base & Surface Course
(Dolomitic Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.81	Special Embankment (non-plastic)
Water Absorption = 0.4%	Asphaltic Surface Treatment
Updated = 5/31/2022	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**APS00014560 Shorline Aggregates Inc. - South Brook Quarry****Material****Approved Uses**

Granite	Base & Surface Course
Spec. Gravity-SSD = 2.71	Granular Material for Subbase
Water Absorption = 0.5%	Special Embankment (non-plastic)
Updated = 4/7/2021	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

## APS00014700 Heidelberg Materials-Servtex Quarry-New Braunfels

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
F.K.A. Hanson Aggregates	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.57	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 5/22/2023	(Friction Rating = IV)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(excluding bridge decks)
	Riprap & Stone Revetment

## APS00014710 Arcosa Lightweight - Livingston, AL

<u>Material</u>	<u>Approved Uses</u>
Lightweight Aggregate	Special Embankment (non-plastic)
(Expanded Clay)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 1.07	Asphaltic Concrete
Water Absorption = 20.8%	(Friction Rating = I)
Updated = 12/8/2021	Portland Cement Concrete

## Out of State

## APS00014740 Heidelberg Materials - Burnet Quarry

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
F.K.A. Hanson Aggregates -	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absorption = 0.6%	Asphaltic Concrete
Updated = 5/22/2023	(Friction Rating = IV)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

## APS00014900 Neely's Landing LLC.- Jackson, MO

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 10/20/2021	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00014980 Arcosa Lightweight - Streetman Plant****Material**

Lightweight Aggregate

(Expanded Shale)

Spec. Gravity-SSD = 1.65

Water Absorption = 14.1%

Updated = 12/2/2022

**Approved Uses**

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = I)

Portland Cement Concrete

**APS00015020****APAC Brickey Stone - Bloomdale - Kimmswick****Material**

Stone

(Limestone)

Spec. Gravity-SSD = 2.67

Water Absorption = 1.3%

Updated = 6/24/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV)

Portland Cement Concrete

(may be used on bridge decks)

Riprap &amp; Stone Revetment

**APS00015110****Lafarge Aggregates-Cave-In-Rock, IL-Dolomite Ledge****Material**

Stone

(Dolomitic Limestone)

Spec. Gravity-SSD = 2.67

Water Absorption = 1.1%

Updated = 6/24/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV)

Portland Cement Concrete

(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

(may be used on bridge decks)

Riprap &amp; Stone Revetment

**APS00015120****Lafarge Aggrs-Cave-In-Rock, IL-Upper St. Gen Ledge****Material**

Stone

(Limestone)

Spec. Gravity-SSD = 2.67

Water Absorption = 0.9%

Updated = 6/24/2022

**Approved Uses**

Base &amp; Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV)

Portland Cement Concrete

(may be used on bridge decks)

Riprap &amp; Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

Out of State

**APS00015130 Lafarge Aggs - Cave-In-Rock, IL - Transition Ledge**

<u>Material</u>	<u>Approved Uses</u>
Sand	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.3%	Asphaltic Concrete
Updated = 6/20/2022	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00015230 Shoreline Agg., Inc. - Point Rousse Quarry**

<u>Material</u>	<u>Approved Uses</u>
Granite	Base & Surface Course
Spec. Gravity-SSD = 2.79	Granular Material for Subbase
Water Absorption = 0.4%	Special Embankment (non-plastic)
Updated = 5/4/2022	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = III)
	Portland Cement Concrete
	Riprap & Stone Revetment

Out of State

**APS00015310 Hastie Mining and Trucking #2 - Cave-In-Rock, IL**

<u>Material</u>	<u>Approved Uses</u>
Sand	Base & Surface Course
Stone	Granular Material for Subbase
(Siliceous Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Updated = 7/29/2022	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00015390 Matco Aggregates LLC. - Actopan Quarry - Basalt**

<u>Material</u>	<u>Approved Uses</u>
Granite	Base & Surface Course
Spec. Gravity-SSD = 2.87	Granular Material for Subbase
Water Absorption = 2.1%	Special Embankment (non-plastic)
Updated = 12/12/2023	Asphaltic Surface Treatment
	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	Riprap & Stone Revetment

**B. OTHER AGGREGATE MATERIALS**

## Out of State

**APS00015610 CEMEX 4200 Balcones Quarry - New Braunfels, TX****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.58	Asphaltic Surface Treatment
Water Absorption = 1.5%	Asphaltic Concrete
Updated = 8/16/2023	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00015630 Lafarge Aggrs-Cave-In-Rock, IL - Downeys Bluff Led****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 1.1%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

**APS00015640 Coastal Industrial Resources, LLC-Gibralgar Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.6%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00015720 GCA Materials - May Pen, Jamaica****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV)
	Riprap & Stone Revetment

**APS00015790 Cemex Materials Newfoundland, Inc. - Canada****Material****Approved Uses**

Stone	Base & Surface Course
(Dolomitic Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.75	Asphaltic Surface Treatment
Water Absorption = 0.4%	Asphaltic Concrete
Updated = 11/13/2023	(Friction Rating = IV)
	Riprap & Stone Revetment



**B. OTHER AGGREGATE MATERIALS**

Out of State

APS00015840

Souter Limestone and Minerals, LLC. - Gore, OK

**Material**

**Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Surface Treatment
Updated = 1/12/2024	Asphaltic Concrete
	(Friction Rating = IV)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

**NOTES:**

**Note B-1:**

Refer to Subsections 501.02 and 1003.06 for definition and application of Friction Ratings.

**Note B-2:**

All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

**REFERENCE:**

- DOTD Standard Specifications and Special Provisions, Section 1003
- DOTD Supplemental Specifications
- DOTD Maintenance Specifications

**No information contained in this list is to be used for promotional purposes.**