

By: 

**LOUISIANA  
DEPARTMENT OF TRANSPORTATION AND DEVELOPMENT  
SPECIFICATIONS**

**AGGREGATE, EXPANDED CLAY, 3/16 INCH  
FOR CRACK SEALING**

**DESCRIPTION:**

These specifications cover Expanded Clay Aggregate for use in crack sealing in asphaltic pavement and Portland Cement Concrete Pavement.

**REQUIREMENTS:**

The material shall conform to the following gradation and shall be from an approved source listed on Approved Materials List (AML) for Aggregates.

<u>U.S. SIEVE</u>	<u>% PASSING</u>
3/4 Inch	100
1/2 Inch	100
3/8 Inch	100
No. 4	95 – 100
No. 8	35 – 80
No. 16	15 – 50
No. 30	5 – 30
No. 50	0 – 20
No. 100	0 – 15

**SAMPLING:**

Sampling will be in accordance with the Materials Sampling Manual.