

SPECIFICATIONS GRADATION FOR #57 LIMESTONE

GRADATION SIEVE SIZE	%	PASSING
1-1/2" (37.5 MM)	100	100
1" (25.0 MM)	95	100
1/2" (12.5 MM)	25	60
#4 (4.75 MM)	0	10
#8 (2.36 MM)	0	5

SPECIFIC GRAVITY (ASTM C 127 AASHTO T-85)

BULK DRY	2.64
SATURATED SURFACE DRY	2.67
APPARENT	2.71
ABSORPTION	1.00

LOS ANGELES ABRASION (ASTM C 131 AASHTO T-96)

GRADING	A
% LOSS	27.00

UNIT WEIGHT - LBS PER CUBIC FOOT (ASTM C 29 AASHTO T-19)

DRY LOOSE	81.00
DRY RODDED	92.00

SODIUM SULFATE SOUNDNESS (ASTM C 88 AASHTO T-104)

% LOSS	3.50
--------	------