

APPROVED MATERIALS LIST

AGGREGATES

Aggregates from the following sources have demonstrated the capability to conform to the quality requirements of Section 1003 of the Department's Standard Specifications for Roads and Bridges, except as noted.

See 'Endnotes' and 'Notes' at the end of each section.

A. CHERT GRAVEL AND SILICA SANDS

Chert gravels on this list have a Friction Rating of III when used as a coarse aggregate for Asphaltic Concrete. Friction Ratings are defined in Subsection 1003.06

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT

District 03

APS00006160 (A309) Dupont Sand, LLC-Carencro, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00006550 (A308) L & W Sand Pit, LLC-Carencro, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00007310 (A310) Vermillion Shell & Limestone Co. Inc.-Maurice, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Maurice	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00011660 (A311) Perero Co. DBA-DND Landscape - Broussard, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Broussard	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00011760 (A312) Lafayette Sand & Fill - Lafayette, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Carencro	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 03****APS00012000****Red Hawk Materials - Maurice, LA****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Maurice

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00012170**Red Hawk Materials, LLC - Carencro, LA****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Carencro

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00012630**Glenn Lege Construction - Youngsville****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 1/12/2024

APS00015080**B & D Materials, LLC - Parks, LA****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 4/7/2022

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

District 04**APS00006830 (A428) MRH Sand & Gravel-Benton, LA****Material**

Gravel

Approved Uses

Granular Material for Subbase

Benton

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.60

Asphaltic Surface Treatment

Water Absportion = 1.0%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Benton

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Water Absportion = 0.5%

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 04****APS00007000 (A427) South Land Sand-Ringgold, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel Only	Base & Surface Course
Ringgold	Granular Material for Subbase
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Updated = 8/25/2017	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete

APS00011330 (A429) Blount Brothers Construction, Inc. -Shreveport, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Blout Bros. Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00011910 Hat Creek Dirt Pit - Bossier City, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 2/17/2017	Portland Cement Concrete

APS00012310 SiteWurx Sand - Sibley, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Sibley - 164 Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00012660 Skyplex Trucking -Bentley, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Wallace Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

District 05**APS00006000 (A509) Century Ready Mix - West Monroe, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Jonesboro Road	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 05****APS00007270 (A502) Martin Marietta - Perryville, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Perryville	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Perryville	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

APS00014950 Star Silica LLC. - West Monroe, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

APS00015510 G & W Sand & Gravel, LLC. - West Monroe

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 6/20/2023	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

District 07**APS00006130 (A712) DSD Energy Services-Oakdale, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Oakdale Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00006520 (A710) Kinder Sand Co.-Kinder, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Kinder	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 07****APS00007320 (A709) Village Sand, Inc.-Kinder, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Indian Village	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

APS00012100 Lake Area Materials, LLC - DeRidder

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absportion = 1.7%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)

Updated = 3/21/2017

APS00012190 Elite Sand - Longville, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete

Updated = 4/13/2017

APS00012390 Gator Aggregates - Deridder, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pippin Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pippin Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

APS00014360 Arcosa Aggregates - Anacoco Plant 1391-Merryville

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.55	Granular Material for Subbase
Water Absportion = 1.0%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)

Updated = 8/3/2022

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 07****APS00014370****Arcosa Aggregates - Indian Village Plant 1325****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 7/29/2022

Portland Cement Concrete

APS00014470**Merryville Aggregate, LLC - Evans, LA****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.56

Granular Material for Subbase

Water Absportion = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/12/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00014890**South Coast Materials, LLC. - Longville****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 5/7/2024

APS00014960**Arcosa Aggregates - Eaves Loop - Plant 1328****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.73

Granular Material for Subbase

Water Absportion = 1.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/18/2025

Portland Cement Concrete

APS00015140**Arcosa Aggregates - Plant LA 1343 - DeRidder****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.57

Granular Material for Subbase

Water Absportion = 0.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 08****APS00007150 (A844) Tanner Heavy Equipment Co-Leesville, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Tanner Pit #2	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/25/2017

APS00007300 (A822) Martin Marietta - Woodworth, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	(Friction Rating = III - Coarse Agg. Only)
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017
(Gravel from this source contains an unusual amount of hematite iron ore, if used in Portland Cement Concrete, the hematite content cannot exceed 2%)**APS00011680 (A847) Larry Grayson & Son Trucking, LLC -Forest Hill, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Ahtus Melder Rd Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.57	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Ahtus Melder Rd Pit	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 8/22/2017

APS00011710 (A849) Diamond B Construction Co.,LLC - Boyce, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Hot Wells / Gardener Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00011720 (A850) Diamond B Construction Co., LLC Woodworth, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Woodworth Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Concrete
Water Absportion = 0.2%	Portland Cement Concrete
Updated = 5/7/2024	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 08****APS00014440****Cenla Materials - Forest Hill, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absportion = 1.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/25/2020

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00016060**Larry Grayson & Son Trucking, LLC #2-Forest Hill****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 4/14/2025

District 58**APS00007130****(A914) Swim Enterprises-Columbia, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Columbia

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00007290**(A913) Martin Marietta - Jena, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Jena

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absportion = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Jena

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absportion = 0.5%

(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 58****APS00011810 (A916) Pokey's Materials - Olla, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
F.K.A. Amberg Construction	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
F.K.A. Amberg Construction	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	
F.K.A. Amberg Construction	

Updated = 2/24/2025

APS00015030 Amberg Construction, LLC. - Olla

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 1.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 4/7/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00015090 D & J Construction Co., LLC - Aimwell, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 4/7/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

District 61**APS00002200 (A628) Bear Industries - Port Allen, LA**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Port Allen	
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00005950 (A646) Bunch Sand and Gravel #1 - Clinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pit #1	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.3%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pit #1	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 7/26/2018

APS00006180 (A636) Feliciana Farms, Inc.-St. Francisville, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Bayou Sara	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Bayou Sara	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

APS00006400 (A632) Hooper Road Dirt Pit-Baton Rouge, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Baton Rouge	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00007010 (A640) Southern Aggregates, LLC-Norwood,LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Felps	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Felps	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00011640 (A644) Fleniken Sand & Gravel Inc - Clinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Acme Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 1.9%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Acme Pit	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 7/26/2018

APS00011650 (A645) Dolese Bros-St.HelenaSand&Gravel - Pine Grove, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
St. Helena S&G Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.6%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
St. Helena S&G Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 6/3/2020

APS00011920 Regional Sand & Gravel - Clinton, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Highway 960 Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Highway 960 Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

APS00012530 Dennis Stewart Equipment Rental,Inc Baton Rouge,LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Joor Road Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/22/2017

APS00012910 South Louisiana Fill Materials, LLC - Darrow, LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 1/5/2024

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00014150 Lionel Boudreaux Trucking, LLC - St. Francisville**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 10/16/2019	Portland Cement Concrete

APS00014180 Ivey Enterprises, LLC - Greenwell Springs, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absportion = 2.7%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 10/16/2019	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00014850 Superior Sand & Gravel - Plant 1 - Clinton, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.57	Granular Material for Subbase
Water Absportion = 0.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 10/5/2021	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00014860 Superior Sand & Gravel - Plant 2 - Clinton

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 10/5/2021	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00015000 Barriere Construction Co. LLC - Map Pit**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.49	Granular Material for Subbase
Water Absportion = 3.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete - Gravel Only

APS00015150 Arcosa Aggregates - Plant LA 1342 - Clinton Pit

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/3/2022	Portland Cement Concrete

APS00015490 South Louisiana Fill Materials LLC - Convent

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 1/5/2024

APS00015520 Superior Sand & Gravel - Plant 3 - Greenwell Sprgs

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 1.9%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

APS00016130 Magnolia Sand Gravel Soil - Denham Springs

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.65	Asphaltic Concrete
Water Absportion = 0.2%	(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00016140 Convent Minority Material Supplier LLC #2**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 2.3%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.65	Asphaltic Concrete
Water Absportion = 0.1%	(Friction Rating = III - Coarse Agg. Only)
Updated = 2/24/2025	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00016210 Ivey Dirt & Aggregates - Greenwell Springs

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.65	Special Embankment (non-plastic)
Water Absportion = 0.2%	Asphaltic Concrete

Updated = 12/4/2024

District 62**APS00005700 (AX04) Accardo Materials, Inc-Franklinton,LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Isabel	Granular Material for Subbase
Spec. Gravity-SSD = 2.57	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Isabel	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/22/2017

APS00005870 (AY06) Lakeview Sand & Gravel - Bogalusa, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Bogalusa	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Bogalusa	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00005990 (AY10) Cash Sand & Gravel, Inc.-Denham Springs, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Easterly Plant	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Easterly Plant	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 7/26/2018

APS00006060	Crawford Aggregate Industr-Pine Grove,LA - Jenkins
<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Jenkins Lane	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Jenkins Lane	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 6/3/2020

APS00006100 (AX71) Daley Sand & Gravel, Inc.-Roseland,LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Roseland	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Roseland	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
Roseland	

Updated = 3/12/2025

APS00006170 (AY17) Brownstone Sand & Gravel - Franklinton, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Enon Plant - Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Enon Plant - Franklinton	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete - Gravel Only
Water Absportion = 0.5%	

Updated = 10/26/2021

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006190 (AY24) Florida Parishes Aggregate-Fluker, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Kent Pit - Fluker	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Kent Pit - Fluker	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006240 (AX91) Gillman Enterprises, LLC-Independence, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Independence	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Independence	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006350 (AY14) Hard Rock Sand & Gravel LLC - Franklinton, LA - #2

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
#2 - Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#2 - Franklinton	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006360 (AX89) Hard Rock Sand & Gravel, LLC-Mt. Hermon, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Mt. Hermon	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Mt. Hermon	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006450 (AX72) Industrial Aggregates, LLC-Franklinton, LA-Pine CI**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

APS00006510 (AX68) K & C Gravel-Independence,LA

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete

APS00006590 (AY03) Amrize Inc. - Honey Island

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Honey Island	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.51	Asphaltic Surface Treatment
Water Absportion = 2.5%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Honey Island	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	
Honey Island	

Updated = 3/12/2025

APS00006600 (AY01) Amrize Inc. - Bogalusa,LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Isabel	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Isabel	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006670 (AX43) Lon Land Gravel Co.-Mt Hermon, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklin	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absorption = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklin	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

APS00006770 (A135) Mears Sand & Gravel-Denham Springs, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Dennis Mills	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Dennis Mills	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Water Absorption = 0.5%	

Updated = 6/3/2020

APS00006850 (AY12) P & J Sand & Gravel, LLC-Independence, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Independence	Granular Material for Subbase
Spec. Gravity-SSD = 2.48	Special Embankment (non-plastic)
Water Absorption = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Independence	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	

Updated = 8/24/2017

APS00006920 (AX29) Ram Industries-Mt. Hermon, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklin	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absorption = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklin	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absorption = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006990 (AX69) Smith Sand & Gravel-Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklinton	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00007030 (AY26) Southern Aggregates, LLC-Denham Springs, LA-Plant 7

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Plant #7	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 1.8%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Plant #7	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 7/26/2018

APS00007140 (AX96) T & D Sand & Gravel, LLC-Independence, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Amite	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Amite	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00007490 (AB98) Willis Sand & Gravel-Bogalusa, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Sun	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 2.5%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Sun	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00011340 (AY29) BMS, LLC - Amite, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Amite Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Amite Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/22/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011410 (AX75) Hard Rock Sand & Gravel LLC - Franklinton, LA - #1

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
#1 Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.51	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#1 Franklinton	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011460 (AY30) Hunt Gravel - Franklinton, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Franklinton	Granular Material for Subbase
Spec. Gravity-SSD = 2.51	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Franklinton	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00011520 (AY31) Industrial Mining Plant 5 - Tickfaw, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Black Cat Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Black Cat Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/25/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00011700 (AY34) Madden Roseland, LA Gravel Pit - Roseland, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Formerly Diamond B	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.1%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Formerly Diamond B	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
Formerly Diamond B	

Updated = 1/26/2023

APS00011790 (AY32) Southern Aggregates - Amite, LA - #9

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Plant #9	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.52	Asphaltic Surface Treatment
Water Absportion = 2.3%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Plant #9	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 8/6/2018

APS00011800 (AY33) Bunch's Sand and Gravel #2 - Greensburg, LA

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Pit #2	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absportion = 1.8%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Pit #2	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	
Water Absportion = 0.5%	

Updated = 7/26/2018

APS00011940 Baldwin Redi-Mix Co. Inc.-Greensburg, H&L Island Pit

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 1.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 7/26/2018	Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00012340****River Road Rock - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Mt. Hermon Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Mt. Hermon Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

APS00012420**Tate Construction, LLC - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Tate Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Tate Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00012510**Industrial Aggregates, LLC - Covington, LA - #2**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Enon Plant #2	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Enon Plant #2	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

APS00012620**Industrial Aggregates - Franklinton, LA**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pine Cliff Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pine Cliff Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00013080 Northern Sand & Gravel, L.L.C. - Independence**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absportion = 2.4%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 4/29/2020	Portland Cement Concrete

APS00013250 R & S Dozer Service, LLC - Franklinton

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 1.7%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 10/22/2021	Portland Cement Concrete - Gravel Only

APS00013390 L & C Gravel, LLC - Plant #6 - Fluker

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 1.9%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 9/12/2019	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00014300 Southern Aggregates, LLC Plant 31 - Franklinton

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	(Friction Rating = III - Coarse Agg. Only)
Water Absportion = 0.5%	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 7/16/2020	

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62**

APS00014350	Barriere Construction Co., LLC - Independence, LA
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 7/15/2020	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00014410	Arcosa Aggregates - Pearl River Plant 1725
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absportion = 3.3%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/3/2022	Portland Cement Concrete

APS00014780	Cash Sand & Gravel, Inc. - Kemp Plant -D.S., LA
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.1%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 10/5/2021	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00014990	Barriere Construction Co. LLC - Miley Pit
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 2/22/2022	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00015160 Arcosa Aggregates - Plant LA 1349 - Pearl River**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.49	Granular Material for Subbase
Water Absportion = 3.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/4/2022	Portland Cement Concrete

APS00015170 Arcosa Aggregates - Plant LA 1341 - Independence

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/4/2022	Portland Cement Concrete

APS00015200 Arcosa Aggregates - Plant LA 1345 - Franklinton

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.49	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/4/2022	Portland Cement Concrete

APS00015210 Arcosa Aggregates - Plant LA 1340 - Denham Springs

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.1%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/4/2022	Portland Cement Concrete

APS00015410 Crawford Aggregate Industries - Cross Pit

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62**

APS00015460	Louisiana Aggregate Materials, LLC-Denham Springs
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 2.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 2/18/2025	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00015530	Tri-Parish Sand & Gravel, LLC. - Denham Springs
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.52	Granular Material for Subbase
Water Absportion = 2.0%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 1/5/2026	Portland Cement Concrete

APS00015650	Accardo Mining, LLC. - Bogalusa
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.19	Granular Material for Subbase
Water Absportion = 2.3%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete - Gravel Only

APS00015670	Candies Excavation, Inc. - Folsom
Material	Approved Uses
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 1/12/2024	

APS00015680	A-1 Aggregates - KSB Holdings, LLC - Mt. Hermon
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absportion = 2.6%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete - Gravel Only

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00015890****M & M Gravel - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absportion = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete - Gravel Only

APS00015980**River Road Materials, LLC. - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absportion = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete - Gravel Only

APS00016070**BearCo Construction, LLC. - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absportion = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Water Absportion = 4.2%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00016300**Crawford Aggregate Industries - Lee Brown Pit****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absportion = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.60

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 9/23/2025

Portland Cement Concrete - Gravel Only

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00005730 (ASAN) Alabama Sand and Gravel-Prattville, AL**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Billingsley Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.63	Special Embankment (non-plastic)
Water Absportion = 0.8%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Billingsley Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00005740 (ASAV) Alliance Sand and Gravel, LLC-Phil Campbell, AL

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Special Embankment (non-plastic)
Phil Campbell Pit	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00005750 (ASAK) Allstate Deatsville, LLC-Deatsville, AL

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Deatsville Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00005780 (ABAO) Arkansas Gravel Company, Inc.-Hampton, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Bradshaw Mine	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Bradshaw Mine	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00005790 (AB76) B & B Gravel & Trucking Co.-Bearden, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.55	Granular Material for Subbase
Water Absportion = 1.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00005830 (ASAR) Baldwin Sand & Gravel-Crystal Springs, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Crystal Springs Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.57	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Crystal Springs Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00005920 (ASAM) Blackwell Aggregates, Inc.-Nicholson, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Jackson Landing Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.48	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Jackson Landing Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00005930 (AB31) Blain Sand & Gravel, Inc.-Natchez, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Coverhill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.57	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Coverhill Pit	Portland Cement Concrete
Spec. Gravity-SSD = 2.62	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00005940 (AA57) Blain Sand & Gravel, Inc.-Crystal Springs, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absportion = 1.7%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006030****Cossatot Rock, LLC-Lockesburg, AR****Material****Approved Uses**

Gravel	Base & Surface Course
Old Deirks Hwy Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Old Deirks Hwy Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.59	Portland Cement Concrete
Water Absportion = 1.0%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00006110 (AA80) Dickerson & Bowen Riverside Gravel-Tylertown, MS**Material****Approved Uses**

Gravel	Base & Surface Course
McComb	Granular Material for Subbase
Spec. Gravity-SSD = 2.46	Special Embankment (non-plastic)
Water Absportion = 4.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
McComb	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006200 (ASAT) Foley Materials Co.-Phenix City, AL- Plant 501**Material****Approved Uses**

Sand Only	Granular Material for Subbase
Plant 501	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006210 (ASAJ) Foley Materials Co.-Phenix City, AL- Plant 505**Material****Approved Uses**

Sand Only	Granular Material for Subbase
Plant 505	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006230 (ASAI) Fouke Sand & Gravel, LLC-Fouke, AR**Material****Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.61	Granular Material for Subbase
Water Absportion = 0.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006260 (ABAK) Green Brothers Gravel Co.-Hazlehurst, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
#22	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#22	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006270 (ABAL) Green Brothers Gravel Co.-CrystalSprings, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
#65	Granular Material for Subbase
Spec. Gravity-SSD = 2.50	Special Embankment (non-plastic)
Water Absportion = 3.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
#65	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006290 (ASAW) Hallet Materials-Porter,TX

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Porter Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete

APS00006300 (ASAU) Hammett Gravel Company, Inc.-Bentonia, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Yazoo City Operation	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Yazoo City Operation	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006310 (AA70) Hanson Aggregates-Bearden, AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Eagle Mills	Granular Material for Subbase
Spec. Gravity-SSD = 2.57	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Eagle Mills	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 8/24/2017

APS00006320 (A092) Heidelberg Materials - Little River Plant

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Little River F.K.A. Hanson	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Little River F.K.A. Hanson	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	
Little River F.K.A. Hanson	

Updated = 3/12/2025

APS00006420 (AB07) Huey Stockstill, LLC - Picayune, MS - 12 Oaks

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
12 Oaks Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
12 Oaks Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

APS00006430 (AB26) Huey P. Stockstill, LLC -Picayune, MS - Pine Grove

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Pine Grove Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Special Embankment (non-plastic)
Water Absportion = 2.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Pine Grove Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006490 (ABAP) JJ Ferguson Sand & Gravel-Cruger, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Blackhawk Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.54	Special Embankment (non-plastic)
Water Absportion = 1.7%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Blackhawk Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/24/2017

APS00006500 (A091) Johnsville Sand & Gravel-Hermitage, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Spec. Gravity-SSD = 2.55	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Spec. Gravity-SSD = 2.62	(Friction Rating = III - Coarse Agg. Only)
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006530 (ASAG) King Sand & Gravel-Kerens, TX

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete

APS00006540 (AB91) Krystal Gravel, Inc.-Crystal Springs, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

APS00006680 (ASAL) Marion Clay & Gravel, LLC-Columbia, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absportion = 3.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006700 (ABAS) Martin Marietta Aggregates-Eagletown, OK**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Broken Bow Sand & Gravel	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Asphaltic Surface Treatment
Water Absportion = 1.2%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Broken Bow Sand & Gravel	Portland Cement Concrete - Gravel Only
Spec. Gravity-SSD = 2.74	
Water Absportion = 0.4%	
Broken Bow Sand & Gravel	

Updated = 7/18/2023

APS00006720 (ASAX) Martin Marietta Aggregates-Garwood, TX

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Garwood Plant	Granular Material for Subbase
Spec. Gravity-SSD = 2.57	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Garwood Plant	(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

APS00006780 (ABAC) Memphis Stone & Gravel Co.-Nesbit, MS

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Anderson Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006790 (ABAD) Memphis Stone & Gravel Co.-Senatobia, MS

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Perry Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006840 (ASAQ) ODDEE Smith Constr.Inc.-Brookhaven, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Oddee California Camp Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Oddee California Camp Pit	(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006860 (A018) Perkinston Sand & Gravel-Perkinston, MS**

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete

APS00006910 (ASAF) R & R Logging & Gravel-Columbia, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.49	Granular Material for Subbase
Water Absportion = 3.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

APS00006930 (ASAP) Riverside Sand & Gravel-Tylertown, MS

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
NW St. Paul Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00006980 (ASAY) Simpson Materials Co.-Valley Park, MO

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Ranken Site	Granular Material for Subbase
Spec. Gravity-SSD = 2.51	Special Embankment (non-plastic)
Water Absportion = 2.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Ranken Site	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/28/2017	Portland Cement Concrete

APS00007160 (AB15) Texas Crushed Stone Co., Inc.-Georgetown, TX

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.48	Asphaltic Surface Treatment
Water Absportion = 3.6%	Asphaltic Concrete
Updated = 3/12/2025	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00007170 (AB27) The Fordyce Co-Victoria, TX**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Briggs Plant	Granular Material for Subbase
Spec. Gravity-SSD = 2.74	Special Embankment (non-plastic)
Water Absportion = 0.8%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Briggs Plant	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

Updated = 8/28/2017

APS00007210 (ASAH) Triangle Aggregates, LLC-Jackson, AL

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Couch - Triangle Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.61	Special Embankment (non-plastic)
Water Absportion = 0.8%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Couch - Triangle Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.63	Portland Cement Concrete

Updated = 8/28/2017

APS00007250 (ASAE) Trinity Materials-West Lockesburg, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.56	Granular Material for Subbase
Water Absportion = 1.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/28/2017	Portland Cement Concrete

APS00007510 (ASAA) Wooten Sand & Gravel-Fouke, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.60	Granular Material for Subbase
Water Absportion = 1.0%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

APS00011350 (ASAS) Eastern Oklahoma Quarries, LLC - Spiro, OK

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spiro Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00011360 (ASAZ) Shale Support Holdings, LLC - Nicholson, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Granular Material for Subbase
Nicholson Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.49	Asphaltic Surface Treatment
Water Absportion = 3.5%	Asphaltic Concrete
Sand	(Friction Rating = III - Coarse Agg. Only)
Nicholson Pit	Portland Cement Concrete
Spec. Gravity-SSD = 2.63	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
Updated = 8/28/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011380 (ASBA) South Gate Aggregates, LLC - Nicholson, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Burge Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absportion = 3.5%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Burge Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.63	Portland Cement Concrete
Updated = 8/28/2017	(Gravel from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011450 (ASBC) Huey P. Stockstill, LLC- Nicholson, MS

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Santa Rosa Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Updated = 8/24/2017	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011470 (ASBB) Eastern Oklahoma Quarries - Garland, AR

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Chieftan Sand Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Concrete
Water Absportion = 0.8%	Portland Cement Concrete
Updated = 8/24/2017	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00011630 (ASBE) Heidelberg Materials - Bristol Plant

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Bristol Plant F.K.A. Hanson	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Portland Cement Concrete
Updated = 5/22/2023	

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00011690 (ASBF) Hammett & Green Aggregates - Vicksburg, MS**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Henry Mine Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 1.2%	Asphaltic Surface Treatment
Sand	Asphaltic Concrete
Henry Mine Pit	(Friction Rating = III - Coarse Agg. Only)
Spec. Gravity-SSD = 2.62	Portland Cement Concrete
Water Absportion = 0.5%	

Updated = 1/8/2019

APS00012160 Dickerson & Bowen Co., Inc - Brookhaven, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel Only	Base & Surface Course
D & B Brookhaven Pit	Granular Material for Subbase
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absportion = 2.2%	Asphaltic Concrete
Updated = 8/28/2017	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete

APS00012380 LeHigh Hanson - Garwood, TX

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Arena Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

APS00012890 D & J Construction Company, LLC - West Monroe

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.5%	Asphaltic Concrete
Updated = 1/16/2018	Portland Cement Concrete

APS00012930 Regional Sand & Gravel, LLC #2 - Clinton

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absportion = 1.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 7/26/2018	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00012980****Gulf Coast Sand & Gravel - Jackson, AL****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.59

Granular Material for Subbase

Water Absportion = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Updated = 1/16/2018

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

APS00013340**Heritage Sand and Gravel - Columbia, MS****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absportion = 3.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/7/2020

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)

APS00014030**Sierra FRAC Sand - Plain Dealing****Material**

Sand Only

Approved Uses

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absportion = 0.5%

Asphaltic Concrete

Updated = 11/15/2018

Portland Cement Concrete

APS00014570**Arkansas Granufill Supply - Hot Springs, AR****Material**

Sand Only

Approved Uses

Asphaltic Concrete

Spec. Gravity-SSD = 2.59

Supplemental Fines (screenings) for Asphaltic Concrete

Water Absportion = 1.5%

Updated = 10/5/2021

APS00014750**Rock Island Sand and Gravel - Harrell Pit-Hampton****Material**

Gravel

Approved Uses

Base & Surface Course

Spec. Gravity-SSD = 2.58

Granular Material for Subbase

Water Absportion = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absportion = 1.0%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/5/2021

Portland Cement Concrete

(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00014970****Gulf Coast Sand - Nicholson, MS****Material****Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.48	Granular Material for Subbase
Water Absportion = 2.9%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.68	Asphaltic Concrete
Water Absportion = 0.1%	(Friction Rating = III - Coarse Agg. Only)
Updated = 1/27/2022	Portland Cement Concrete
	(Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00015010**Island Sand & Gravel - Crossett, AR****Material****Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.51	Granular Material for Subbase
Water Absportion = 1.8%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.64	Asphaltic Concrete
Water Absportion = 0.2%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete - Gravel Only

APS00015130**Amrize Inc. - Cave-In-Rock, IL - Transition Ledge****Material****Approved Uses**

Gravel	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 1.3%	Asphaltic Concrete
Updated = 9/29/2025	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00015180**Arcosa Aggregates - Plant 1347 - Hattiesburg, MS****Material****Approved Uses**

Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/4/2022	Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State**

APS00015190	Arcosa Aggregates - Plant 1348 - Columbia, MS
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.53	Granular Material for Subbase
Water Absportion = 2.2%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 5/13/2025	Portland Cement Concrete
APS00015540	Hammett Gravel Company, Inc. - Red Mountain Plant
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.50	Granular Material for Subbase
Water Absportion = 3.1%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.64	Asphaltic Concrete
Water Absportion = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
APS00015780	RockCo Mining, LLC. - Courtland, MS
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.54	Granular Material for Subbase
Water Absportion = 1.6%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.65	Asphaltic Concrete
Water Absportion = 0.4%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete - Gravel Only
APS00015900	Huey P. Stockstill, LLC. - Boone Mine
Material	Approved Uses
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.45	Granular Material for Subbase
Water Absportion = 3.6%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.64	Asphaltic Concrete
Water Absportion = 0.1%	(Friction Rating = III - Coarse Agg. Only)
Updated = 3/12/2025	Portland Cement Concrete (Sand from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State**

APS00016400

West Side Complex - Hayes Quarry

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Sand	Granular Material for Subbase
Stone (Limestone)	Special Embankment (non-plastic) Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.52	Asphaltic Concrete
Water Absportion = 3.2%	(Friction Rating = IV - Coarse Agg. Only)
Updated = 10/3/2025	Riprap & Stone Revetment Bedding Material

NOTES:**Note A-1:**

Source approval samples of gravel and sand are obtained by personnel of the Materials and District Laboratories. The source is defined as the pit or quarry which produces the aggregate being evaluated. All aggregate which does not pass through the 4.75mm (No. 4) sieve shall be source approved prior to use. Certain aggregates may be approved for restricted use. A complete source approval analysis shall be run on each aggregate source.

Note A-2:

All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

Note A-3:

A specific gravity value of 2.62 (SSD) may be used for all in-state silica sands used for portland cement concrete.

Note A-4:

Because absorption has been found to correlate with the type and specific gravity of silica sands and chert gravels, the water absorption factors given in the following table may be used:

B. OTHER AGGREGATE MATERIALS**Out of State****APS00005710 (ABBC) Agrecasa Del Caribe-San Pedro Sula, HON**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.63	Special Embankment (non-plastic)
Water Absportion = 1.6%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

APS00005770 (ABBY) APAC - Brickey's Stone-Bloomsdale, MO - Burlington

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Burlington Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absportion = 1.4%	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only)
Updated = 6/24/2022	Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

APS00005900 (AB25) Arcosa Lightweight - Erwinville, LA

<u>Material</u>	<u>Approved Uses</u>
Lightweight Aggregate	Special Embankment (non-plastic)
(Expanded Clay)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 1.65	(Type B, C, & D applications only)
Water Absportion = 16.3%	Asphaltic Concrete (excluding wearing surfaces)
Updated = 12/8/2021	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete

APS00005960 (ABBU) Arcosa Aggregates - Grand Rivers,KY-StLouis

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
St. Louis Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absportion = 0.5%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 10/20/2021	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00005970 (ABBK) Texas Materials - Burnet.TX**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
F.K.A OldCastle Materials -	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absportion = 0.7%	Asphaltic Concrete
Updated = 1/12/2024	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00006080 (ABBN) Crystal Hill Quarry-North Little Rock, AR

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Granite Mountain Quarries	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absportion = 0.9%	Asphaltic Concrete
Updated = 9/24/2024	(Friction Rating = II - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00006250 (A033) Granite Mountain Quarries-Little Rock, AR

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Syenite Granite	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.59	Asphaltic Surface Treatment
Water Absportion = 0.9%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = II - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006340 (A077) Hanson Aggregates-Perch Hill Plant-Chico, TX

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Perch Hill Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.8%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00006370 (AA90) Hastie Mining Company-Cave-in-Rock,IL**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Hastie Mining Company Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absportion = 0.8%	Asphaltic Concrete
Updated = 8/24/2017	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006440 (AA91) Ideal Domicana, SA-Santo Domingo, DR

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.61	Special Embankment (non-plastic)
Water Absportion = 1.3%	Asphaltic Surface Treatment
Updated = 8/25/2017	Portland Cement Concrete

APS00006480 (ABBO) Amrize Inc. - Jamaica Aggregates Limited

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Crushed Alluvial Stone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.72	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006560 (ABAN) Amrize Inc. - Cave-In-Rock, IL - SandStone

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absportion = 0.8%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00006570 (ABAM) Amrize Inc. - Cave-In-Rock, IL - Sil. Limestn**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Ledge 8 - 10	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = III - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) (may be used on bridge decks) Riprap & Stone Revetment

APS00006580 (ABC) Amrize Inc. - Fredonia, KY

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absportion = 0.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) (may be used on bridge decks) Riprap & Stone Revetment

APS00006690 (AA86) Martin Marietta Aggregates-Bahamas, BAH

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Porous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absportion = 3.9%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only) Portland Cement Concrete Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00006710 (AA92) Martin Marietta Aggregates-Cove, AR**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Rhyolite)	Granular Material for Subbase
Traprock	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absportion = 0.7%	Asphaltic Concrete
Updated = 7/20/2022	(Friction Rating = II - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00006730 (ABAW) Martin Marietta Aggregates-Malvern, AR - SandStone

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Jones Mill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absportion = 2.2%	Asphaltic Concrete
Updated = 8/25/2017	(Friction Rating = II - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

Out of State**APS00006740 (ABAX) Martin Marietta Aggregates-Malvern, AR - Granite**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Jones Mill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.58	Asphaltic Surface Treatment
Water Absportion = 0.9%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006750 (AA39) Martin Marietta Aggregates-Mulgrave, NS

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absportion = 0.9%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(excluding OGFC and coarse mix)
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00006760 (AA51) Martin Marietta Aggregates-Sawyer,OK**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absportion = 2.3%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete (Friction Rating = I - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate) Riprap & Stone Revetment

APS00006880 (AB13) Pine Bluff Sand & Gravel-Delaware, AR

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
River Mountain Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.63	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete (Friction Rating = I - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate) Riprap & Stone Revetment
Updated = 11/10/2020	

APS00006890 (ABBS) Pine Bluff Sand & Gravel-Salem,KY

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Cumberland River Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.8%	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only) Riprap & Stone Revetment
Updated = 10/28/2021	

Out of State**APS00007160 (AB15) Texas Crushed Stone Co., Inc.-Georgetown, TX**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.48	Asphaltic Surface Treatment
Water Absportion = 3.6%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (excluding bridge decks) Riprap & Stone Revetment
Updated = 3/12/2025	

B. OTHER AGGREGATE MATERIALS

APS00007180 (A056) Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn8

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.64	Special Embankment (non-plastic)
Water Absportion = 1.6%	Asphaltic Surface Treatment
Updated = 5/21/2018	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00007190 (A079) Tower Rock Stone Co-St.Genevieve, MO- Oolitic

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Oolitic Stone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.47	Special Embankment (non-plastic)
Water Absportion = 4.8%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

Out of State

APS00007260 (AB61) Martin Marietta - Bridgeport TX

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Bridgeport	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absportion = 1.3%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

APS00007340 (A042) Vulcan Materials Co-Calera, AL

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Calera Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.71	Asphaltic Surface Treatment
Water Absportion = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00007350 (AA95) Vulcan Materials Co-Cancun, MEX**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absportion = 3.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

APS00007380 (ABBQ) Vulcan Materials Co-Grand Rivers,KY- Ft Payne

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Ft. Payne Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.2%	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only)
Updated = 10/29/2021	(Friction Rating = II for ADT <= 20,000 - Coarse Agg. Only)

APS00007390 (ABBP) Vulcan Materials Co-Grand Rivers,KY- Warsaw

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absportion = 0.9%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 10/29/2021	Riprap & Stone Revetment

Out of State**APS00007430 (ABBT) Vulcan Materials Co-Tuscumbia, AL- Pride Quarry**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.60	Special Embankment (non-plastic)
Water Absportion = 1.9%	Asphaltic Surface Treatment Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 6/24/2022	Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) (may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00007450 (AB19) Vulcan Materials Co-Trinity, AL**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Trinity Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 1.2%	Asphaltic Concrete
Updated = 10/25/2017	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00007480 (ABAY) Warren Paving-Salem, KY - Upper Warsaw Formation

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Slats Lucas Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absportion = 0.4%	Asphaltic Concrete
Updated = 10/20/2021	(Friction Rating = III - Coarse Agg. Only)
	(Friction Rating = II for ADT <10,000 - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00007500 (AB78) Winn Materials, Inc.-Clarksville, TN

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absportion = 0.6%	Asphaltic Surface Treatment
Updated = 10/28/2021	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00007520 (AB04) Capital Aggregates - Delta Quarry

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absportion = 2.1%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00011430 (ABCD) APAC - Brickey's Stone-Bloomsdale, MO - Plattin**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Plattin Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absportion = 2.0%	Asphaltic Concrete
Updated = 7/26/2018	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

Out of State**APS00011620 (ABCI) Central Stone Co - Farmington, MO**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Butler Hill Granite Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absportion = 0.3%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00011870 Amrize Inc. - Smithland, KY-Three Rivers-S1

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
3RvrQry-Bench S1-Pit#1	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Updated = 5/20/2020	(Friction Rating = III - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00012130 Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn12

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Ledge 12	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.8%	Asphaltic Concrete
Updated = 11/9/2018	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State**

APS00012300	Vulcan Materials Co-West Loachapoka, AL
-------------	---

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 0.4%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete (excluding bridge decks)
	Riprap & Stone Revetment

APS00012320	Arcosa Aggregates - Grand Rivers,KY-Warsaw
-------------	--

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 1.1%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 11/10/2020	Riprap & Stone Revetment

APS00012600	Martin Marietta - MMR - Hondo, TX
-------------	-----------------------------------

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Medina Rock & Rail Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absportion = 2.2%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 8/29/2017	Riprap & Stone Revetment

Out of State

APS00012680	Warren Paving-Salem, KY-Lower High Calcium Ledge
-------------	--

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Lower Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absportion = 0.7%	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only)
Updated = 6/24/2022	Portland Cement Concrete (may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS

APS00012880

Amrize Inc. - Smithland, KY-Three Rivers-S2

Material

Stone

(Siliceous Limestone)

Spec. Gravity-SSD = 2.69

Water Absportion = 0.8%

Updated = 5/20/2020

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(excluding OGFC and coarse mix)

(Friction Rating = III - Coarse Agg. Only)

Riprap & Stone Revetment

Out of State

APS00012960

APAC R4 ObrusS.A. D.C.V. - Boca Del Rio, Mexico

Material

Stone

(Granite)

Spec. Gravity-SSD = 2.89

Water Absportion = 1.5%

Updated = 2/16/2024

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00013370

Canteras LA Ponderosa S.A. - OoliticStnFormtn -5.1

Material

Stone

(Limestone)

Spec. Gravity-SSD = 2.71

Water Absportion = 1.2%

Updated = 2/21/2024

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014110

Rogers Group - Lacey's Springs Quarry

Material

Stone

(Limestone)

Spec. Gravity-SSD = 2.70

Water Absportion = 0.7%

Updated = 2/14/2020

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS

APS00014340

Amrize Inc. - Smithland, KY-Upper Fredonia

Material

Stone

(Siliceous Limestone)

Spec. Gravity-SSD = 2.70

Water Absportion = 1.0%

Updated = 10/21/2020

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Riprap & Stone Revetment

Out of State

APS00014530

Martin Marietta - Mill Creek - Granite

Material

Stone

(Granite)

Spec. Gravity-SSD = 2.74

Water Absportion = 1.0%

Updated = 2/16/2024

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014540

Martin Marietta - Mill Creek - Limestone

Material

Stone

(Dolomitic Limestone)

Spec. Gravity-SSD = 2.81

Water Absportion = 0.4%

Updated = 5/31/2022

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014560

Shorline Aggregates Inc. - South Brook Quarry

Material

Stone

(Granite)

Spec. Gravity-SSD = 2.71

Water Absportion = 0.5%

Updated = 2/16/2024

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00014700 Heidelberg Materials-Servtex Quarry-New Braunfels**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
F.K.A. Hanson Aggregates	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.57	Asphaltic Surface Treatment
Water Absportion = 2.0%	Asphaltic Concrete
Updated = 5/22/2023	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00014710 Arcosa Lightweight - Livingston, AL

<u>Material</u>	<u>Approved Uses</u>
Lightweight Aggregate	Special Embankment (non-plastic)
(Expanded Clay)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 1.07	Asphaltic Concrete
Water Absportion = 20.8%	(Friction Rating = I - Coarse Agg. Only)
Updated = 12/8/2021	Portland Cement Concrete

Out of State**APS00014740 Heidelberg Materials - Burnet Quarry**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
F.K.A. Hanson Aggregates -	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absportion = 0.6%	Asphaltic Concrete
Updated = 5/22/2023	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00014900 Neely's Landing LLC.- Jackson, MO

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Updated = 10/20/2021	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00014980****Arcosa Lightweight - Streetman Plant****Material**

Material	Approved Uses
Lightweight Aggregate	Asphaltic Surface Treatment
(Expanded Shale)	Asphaltic Concrete
Spec. Gravity-SSD = 1.65	(Friction Rating = I - Coarse Agg. Only)
Water Absportion = 14.1%	Portland Cement Concrete

Updated = 12/2/2022

APS00015020**APAC Brickey Stone - Bloomdale - Kimmswick****Material**

Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absportion = 1.3%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015110**Amrize Inc. - Cave-In-Rock, IL-Dolomite Ledge****Material**

Material	Approved Uses
Stone	Base & Surface Course
(Dolomitic Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absportion = 1.1%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015120**Amrize Inc. - Cave-In-Rock, IL-Upper St. Gen Ledge****Material**

Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absportion = 0.9%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00015130 Amrize Inc. - Cave-In-Rock, IL - Transition Ledge**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 1.3%	Asphaltic Concrete
Updated = 9/29/2025	(Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) Riprap & Stone Revetment

APS00015230 Shoreline Agg., Inc. - Point Rousse Quarry

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.79	Special Embankment (non-plastic)
Water Absportion = 0.4%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete (Friction Rating = III - Coarse Agg. Only) Portland Cement Concrete Riprap & Stone Revetment

APS00015310 Hastie Mining and Trucking #2 - Cave-In-Rock, IL

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absportion = 1.0%	Asphaltic Surface Treatment
Updated = 6/13/2025	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete Riprap & Stone Revetment

APS00015390 Matco Aggregates LLC. - Actopan Quarry - Basalt

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.87	Special Embankment (non-plastic)
Water Absportion = 2.1%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State**

APS00015610	CEMEX 4200 Balcones Quarry - New Braunfels, TX
Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.58	Special Embankment (non-plastic)
Water Absportion = 1.5%	Asphaltic Surface Treatment
Updated = 8/12/2025	Asphaltic Concrete (Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) (may be used on bridge decks) Riprap & Stone Revetment
APS00015630	Amrize Inc. - Cave-In-Rock, IL - Downeys Bluff Led
Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absportion = 1.1%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only) Portland Cement Concrete (Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement) Riprap & Stone Revetment
APS00015640	Coastal Industrial Resources, LLC-Gibralgar Quarry
Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 1.6%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only) Riprap & Stone Revetment
APS00015720	GCA Materials - May Pen, Jamaica
Material	Approved Uses
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absportion = 2.0%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only) Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State**

APS00015790	Cemex Materials Newfoundland, Inc. - Canada
-------------	---

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Dolomitic Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.75	Asphaltic Surface Treatment
Water Absportion = 0.4%	Asphaltic Concrete
Updated = 11/13/2023	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00015840	Souter Limestone and Minerals, LLC. - Gore, OK
-------------	--

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absportion = 0.7%	Asphaltic Surface Treatment
Updated = 1/12/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015850	Amrize, Inc.-Three Rivers Quarry -Smithland, KY S3
-------------	--

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absportion = 1.0%	Asphaltic Concrete
Updated = 1/29/2024	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00015940	Two Countries Materials S.A. DE CV - Mexico
-------------	---

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 2.0%	Asphaltic Concrete
Updated = 3/14/2024	Riprap & Stone Revetment

APS00016010	Tajo Chirripo S.A. - Limon
-------------	----------------------------

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Basalt Rock)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absportion = 1.6%	Asphaltic Concrete
Updated = 6/11/2025	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS

APS00016120

Antoine Rock Quarry - Delight, AR

Material

Stone

(Limestone)

Updated = 9/10/2024

Approved Uses

Riprap & Stone Revetment

Out of State

APS00016400

West Side Complex - Hayes Quarry

Material

Gravel

Sand

Stone

(Limestone)

Spec. Gravity-SSD = 2.52

Water Absportion = 3.2%

Updated = 10/3/2025

Approved Uses

Base & Surface Course

Granular Material for Subbase

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Riprap & Stone Revetment

Bedding Material

APS00016410

Southland Resources, Inc.

Material

Stone

(Sandstone)

Spec. Gravity-SSD = 2.62

Water Absportion = 1.9%

Updated = 7/24/2025

Approved Uses

Base & Surface Course

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Riprap & Stone Revetment

APS00016440

Amrize Agg.-Smithland Three Rivers-Middle Fredonia

Material

Stone

(Limestone)

Spec. Gravity-SSD = 2.64

Water Absportion = 1.7%

Updated = 10/3/2025

Approved Uses

Base & Surface Course

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Riprap & Stone Revetment

Out of State

APS00016450

Eiffage Infraestructuras SA - Cartagena Quarry

Material

Stone

(Limestone)

Spec. Gravity-SSD = 2.78

Water Absportion = 0.8%

Updated = 12/10/2025

Approved Uses

Base & Surface Course

Special Embankment (non-plastic)

Asphaltic Surface Treatment

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State**

APS00016470	Eiffage Infraestructuras SA - La Algueña Quarry
-------------	---

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absportion = 0.6%	Asphaltic Concrete
Updated = 12/11/2025	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

NOTES:**Note B-1:**

Refer to Subsections 501.02 and 1003.06 for definition and application of Friction Ratings.

Note B-2:

All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

REFERENCE:

DOTD Standard Specifications and Special Provisions, Section 1003
 DOTD Supplemental Specifications
 DOTD Maintenance Specifications

No information contained in this list is to be used for promotional purposes.