

APPROVED MATERIALS LIST

AGGREGATES

Aggregates from the following sources have demonstrated the capability to conform to the quality requirements of Section 1003 of the Department's Standard Specifications for Roads and Bridges, except as noted.

See 'Endnotes' and 'Notes' at the end of each section.

A. CHERT GRAVEL AND SILICA SANDS

Chert gravels on this list have a Friction Rating of III when used as a coarse aggregate for Asphaltic Concrete. Friction Ratings are defined in Subsection 1003.06

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT

District 03

APS00006160 (A309) Dupont Sand, LLC-Carencro, LA

Material

Approved Uses

Sand Only

Granular Material for Subbase

Carencro

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00006550 (A308) L & W Sand Pit, LLC-Carencro, LA

Material

Approved Uses

Sand Only

Granular Material for Subbase

Carencro

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00007310 (A310) Lafayette Materials INC.- Maurice, LA

Material

Approved Uses

Sand Only

Granular Material for Subbase

Maurice

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00011660 (A311) Perero Co. DBA-DND Landscape - Broussard, LA

Material

Approved Uses

Sand Only

Granular Material for Subbase

Broussard

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00011760 (A312) Lafayette Sand & Fill - Lafayette, LA

Material

Approved Uses

Sand Only

Granular Material for Subbase

Carencro

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 03****APS00012000 Red Hawk Materials - Maurice, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Maurice

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Maurice

Updated = 4/16/2026

APS00012170 Red Hawk Materials, LLC - Carencro, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Carencro

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00012630 Glenn Lege Construction - Youngsville**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 1/12/2024

APS00015080 B & D Materials, LLC - Parks, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Sand

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Surface Treatment

Updated = 4/16/2026

Asphaltic Concrete

Portland Cement Concrete

District 04**APS00006830 (A428) MRH Sand & Gravel-Benton, LA****Material****Approved Uses**

Gravel

Granular Material for Subbase

Benton

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.60

Asphaltic Surface Treatment

Water Absorption = 1.0%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Benton

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 5/14/2026

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 04****APS00007000 (A427) South Land Sand-Ringgold, LA****Material****Approved Uses**

Gravel Only

Base & Surface Course

Ringgold

Granular Material for Subbase

Spec. Gravity-SSD = 2.60

Asphaltic Surface Treatment

Water Absorption = 1.0%

Asphaltic Concrete

Updated = 8/25/2017

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

APS00011330 (A429) Blount Brothers Construction, Inc. -Shreveport, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Blount Bros. Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00011910 Hat Creek Dirt Pit - Bossier City, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 2/17/2017

Portland Cement Concrete

APS00012310 SiteWurx Sand - Sibley, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Sibley - 164 Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00012660 Skyplex Trucking -Bentley, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Wallace Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

District 05**APS00006000 (A509) Century Ready Mix - West Monroe, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Jonesboro Road

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 05****APS00007270 (A502) Martin Marietta - Perryville, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Perryville

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Perryville

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00014950 Star Silica LLC. - West Monroe, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015510 G & W Sand & Gravel, LLC. - West Monroe**Material****Approved Uses**

Gravel

Base & Surface Course

Sand

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Surface Treatment

Updated = 4/16/2026

Asphaltic Concrete

Portland Cement Concrete

District 07**APS00006130 (A712) DSD Energy Services-Oakdale, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Oakdale Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00006520 (A710) Kinder Sand Co.-Kinder, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Kinder

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 4/16/2026

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 07****APS00007320 (A709) Village Sand, Inc.-Kinder, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Indian Village

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00012100 Lake Area Materials, LLC - DeRidder**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.54

Granular Material for Subbase

Water Absorption = 1.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/21/2017

Portland Cement Concrete

APS00012190 Elite Sand - Longville, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 4/13/2017

Portland Cement Concrete

APS00012390 Gator Aggregates - Deridder, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Pippin Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pippin Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00014360 Arcosa Aggregates - Anacoco Plant 1391-Merryville**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absorption = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/3/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 07****APS00014370 Arcosa Aggregates - Indian Village Plant 1325****Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 7/21/2026

APS00014470 Merryville Aggregate, LLC - Evans, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.56

Granular Material for Subbase

Water Absorption = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/16/2026

Portland Cement Concrete

APS00014890 South Coast Materials, LLC. - Longville**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/4/2026

Portland Cement Concrete - Sand Only

APS00014960 Arcosa Aggregates - Eaves Loop - Plant 1328**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.73

Granular Material for Subbase

Water Absorption = 1.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/18/2025

Portland Cement Concrete

APS00015140 Arcosa Aggregates - Plant LA 1343 - DeRidder**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.57

Granular Material for Subbase

Water Absorption = 0.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 07****APS00015660 Moreau's Sand & Gravel, LLC - Allen****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 3/3/2026

District 08**APS00007150 (A844) Tanner Heavy Equipment Co-Leesville, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Tanner Pit #2

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/25/2017

APS00007300 (A822) Martin Marietta - Woodworth, LA**Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

(Friction Rating = III - Coarse Agg. Only)

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

(Gravel from this source contains an unusual amount of hematite iron ore, if used in Portland Cement Concrete, the hematite content cannot exceed 2%)

APS00011680 (A847) Larry Grayson & Son Trucking, LLC -Forest Hill, LA**Material****Approved Uses**

Gravel

Granular Material for Subbase

Ahtus Melder Rd Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.57

Asphaltic Surface Treatment

Water Absorption = 1.0%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Ahtus Melder Rd Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/22/2017

APS00011710 (A849) Diamond B Construction Co.,LLC - Boyce, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Hot Wells / Gardener Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 08****APS00011720 (A850) Diamond B Construction Co., LLC Woodworth, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Woodworth Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.65

Asphaltic Concrete

Water Absorption = 0.2%

Portland Cement Concrete

Updated = 4/16/2026

APS00014440 Cenla Materials - Forest Hill, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absorption = 1.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/16/2026

Portland Cement Concrete

APS00016060 Larry Grayson & Son Trucking, LLC #2-Forest Hill**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 4/14/2025

District 58**APS00007130 (A914) Swim Enterprises-Columbia, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Columbia

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00007290 (A913) Martin Marietta - Jena, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Jena

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Jena

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 5/14/2026

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 58****APS00011810 (A916) Pokey's Materials - Olla, LA****Material****Approved Uses**

Gravel

Base & Surface Course

F.K.A. Amberg Construction

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

F.K.A. Amberg Construction

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

F.K.A. Amberg Construction

Updated = 2/24/2025

APS00015030 Amberg Construction, LLC. - Olla**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/16/2026

Portland Cement Concrete

APS00015090 D & J Construction Co., LLC - Aimwell, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 4/16/2026

Portland Cement Concrete

District 61**APS00002200 (A628) Bear Industries - Port Allen, LA****Material****Approved Uses**

Sand Only

Asphaltic Concrete

Port Allen

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/22/2017

APS00005950 (A646) Bunch Sand and Gravel #1 - Clinton, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Pit #1

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.3%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pit #1

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 7/26/2018

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00006180 (A636) Feliciana Farms, Inc.-St. Francisville, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Bayou Sara

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Bayou Sara

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00006400 (A632) Hooper Road Dirt Pit-Baton Rouge, LA**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Baton Rouge

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00007010 (A640) Southern Aggregates, LLC-Norwood, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Felps

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Felps

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00011640 (A644) Fleniken Sand & Gravel Inc - Clinton, LA**Material****Approved Uses**

Gravel

Granular Material for Subbase

Acme Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.52

Asphaltic Surface Treatment

Water Absorption = 1.9%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Acme Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 7/26/2018

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00011650 (A645) Dolese Bros-St.HelenaSand&Gravel - Pine Grove, LA****Material****Approved Uses**

Gravel

Base & Surface Course

St. Helena S&G Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.6%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

St. Helena S&G Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 6/3/2020

APS00011920**Regional Sand & Gravel - Clinton, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Highway 960 Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 3.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Highway 960 Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00012530**Dennis Stewart Equipment Rental, Inc Baton Rouge, LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Joor Road Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/22/2017

APS00012910**South Louisiana Fill Materials, LLC - Darrow, LA****Material****Approved Uses**

Sand Only

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 1/5/2024

APS00014150**Lionel Boudreaux Trucking, LLC - St. Francisville****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 10/16/2019

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00014180 Ivey Enterprises, LLC - Greenwell Springs, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 2.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/16/2019

Portland Cement Concrete

APS00014850 Superior Sand & Gravel - Plant 1 - Clinton, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.57

Granular Material for Subbase

Water Absorption = 0.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/5/2021

Portland Cement Concrete

APS00014860 Superior Sand & Gravel - Plant 2 - Clinton**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/5/2021

Portland Cement Concrete

APS00015000 Barriere Construction Co. LLC - Map Pit**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 3.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015150 Arcosa Aggregates - Plant LA 1342 - Clinton Pit**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/3/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00015490 South Louisiana Fill Materials LLC - Convent****Material****Approved Uses**

Sand Only

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 1/5/2024

APS00015520 Superior Sand & Gravel - Plant 3 - Greenwell Sprgs**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.9%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00016130 Magnolia Sand Gravel Soil - Denham Springs**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.65

Asphaltic Concrete

Water Absorption = 0.2%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00016140 Convent Minority Material Supplier LLC #2**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.3%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.65

Asphaltic Concrete

Water Absorption = 0.1%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/24/2025

Portland Cement Concrete

APS00016210 Ivey Dirt & Aggregates - Greenwell Springs**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.65

Special Embankment (non-plastic)

Water Absorption = 0.2%

Asphaltic Concrete

Updated = 12/4/2024

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 61****APS00016710 Ivey Dirt and Aggregates****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 2.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Water Absorption = 0.4%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

District 62**APS00005700 (AX04) Accardo Materials, Inc-Franklinton, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Isabel

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Isabel

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00005870 (AY06) Lakeview Sand & Gravel - Bogalusa, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Bogalusa

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Bogalusa

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

APS00005990 (AY10) Cash Sand & Gravel, Inc.-Denham Springs, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Easterly Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Easterly Plant

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 7/26/2018

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006060 Crawford Aggregate Industr-Pine Grove,LA - Jenkins****Material****Approved Uses**

Gravel

Base & Surface Course

Jenkins Lane

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Jenkins Lane

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 6/3/2020

APS00006100 (AX71) Daley Sand & Gravel, Inc.-Roseland,LA**Material****Approved Uses**

Gravel

Base & Surface Course

Roseland

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Roseland

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Roseland

Updated = 4/15/2026

APS00006170 (AY17) Brownstone Sand & Gravel - Franklinton, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Enon Plant - Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Enon Plant - Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Enon Plant - Franklinton

Updated = 6/17/2026

APS00006190 (AY24) Florida Parishes Aggregate-Fluker, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Kent Pit - Fluker

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Kent Pit - Fluker

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006240 (AX91) Gillman Enterprises, LLC-Independence, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Independence

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Independence

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006350 (AY14) Hard Rock Sand & Gravel LLC - Franklinton, LA - #2**Material****Approved Uses**

Gravel

Base & Surface Course

#2 - Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

#2 - Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006360 (AX89) Hard Rock Sand & Gravel, LLC-Mt. Hermon, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Mt. Hermon

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Mt. Hermon

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006450 (AX72) Industrial Aggregates, LLC-Franklinton, LA-Pine CI**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006510 (AX68) K & C Gravel-Independence,LA****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

APS00006590 (AY03) Amrize Inc. - Honey Island**Material****Approved Uses**

Gravel

Base & Surface Course

Honey Island

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.51

Asphaltic Surface Treatment

Water Absorption = 2.5%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Honey Island

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Honey Island

Updated = 3/12/2025

APS00006600 (AY01) Amrize Inc. - Bogalusa,LA**Material****Approved Uses**

Gravel

Base & Surface Course

Isabel

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Isabel

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006670 (AX43) Lon Land Gravel Co.-Mt Hermon, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00006770 (A135) Mears Sand & Gravel-Denham Springs,LA****Material****Approved Uses**

Gravel

Granular Material for Subbase

Dennis Mills

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.53

Asphaltic Surface Treatment

Water Absorption = 2.0%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Dennis Mills

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 6/3/2020

APS00006850 (AY12) P & J Sand & Gravel, LLC-Independence, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Independence

Granular Material for Subbase

Spec. Gravity-SSD = 2.48

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Independence

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006920 (AX29) Ram Industries-Mt. Hermon, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006990 (AX69) Smith Sand & Gravel-Franklinton,LA**Material****Approved Uses**

Gravel

Base & Surface Course

Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00007030 (AY26) Southern Aggregates, LLC-DenhamSprings,LA-Plant7****Material****Approved Uses**

Gravel

Base & Surface Course

Plant #7

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.52

Asphaltic Surface Treatment

Water Absorption = 1.8%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Plant #7

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 7/26/2018

APS00007140 (AX96) T & D Sand & Gravel, LLC-Independence, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Amite

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Amite

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00007490 (AB98) Willis Sand & Gravel-Bogalusa, LA**Material****Approved Uses**

Gravel

Granular Material for Subbase

Sun

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.52

Asphaltic Surface Treatment

Water Absorption = 2.5%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Sun

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/24/2017

APS00011340 (AY29) BMS, LLC - Amite, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Amite Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Amite Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/22/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00011410 (AX75) Hard Rock Sand & Gravel LLC - Franklinton, LA - #1****Material****Approved Uses**

Gravel

Base & Surface Course

#1 Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.51

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

#1 Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00011460 (AY30) Hunt Gravel - Franklinton, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Franklinton

Granular Material for Subbase

Spec. Gravity-SSD = 2.51

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Franklinton

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00011520 (AY31) Industrial Mining Plant 5 - Tickfaw, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Black Cat Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 3.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Black Cat Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/25/2017

APS00011700 (AY34) Madden Roseland, LA Gravel Pit - Roseland, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Formerly Diamond B

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.1%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Formerly Diamond B

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Formerly Diamond B

Updated = 1/26/2023

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00011790 (AY32) Southern Aggregates - Amite, LA - #9****Material****Approved Uses**

Gravel

Granular Material for Subbase

Plant #9

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.52

Asphaltic Surface Treatment

Water Absorption = 2.3%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Plant #9

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/6/2018

APS00011800 (AY33) Bunch's Sand and Gravel #2 - Greensburg, LA**Material****Approved Uses**

Gravel

Granular Material for Subbase

Pit #2

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.53

Asphaltic Surface Treatment

Water Absorption = 1.8%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Pit #2

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 7/26/2018

APS00011940 Baldwin Redi-Mix Co. Inc.-Greensburg,H&L Island Pit**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 7/26/2018

Portland Cement Concrete

APS00012340 River Road Rock - Franklinton, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Mt. Hermon Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Mt. Hermon Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00012420****Tate Construction, LLC - Franklinton, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Tate Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.52

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Tate Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00012510**Industrial Aggregates, LLC - Covington, LA - #2****Material****Approved Uses**

Gravel

Base & Surface Course

Enon Plant #2

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Enon Plant #2

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00012620**Industrial Aggregates - Franklinton, LA****Material****Approved Uses**

Gravel

Base & Surface Course

Pine Cliff Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pine Cliff Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00013080**Northern Sand & Gravel, L.L.C. - Independence****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absorption = 2.4%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/29/2020

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00013250 R & S Dozer Service, LLC - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00013390 L & C Gravel, LLC - Plant #6 - Fluker**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.9%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 9/12/2019

Portland Cement Concrete

APS00014300 Southern Aggregates, LLC Plant 31 - Franklinton**Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

(Friction Rating = III - Coarse Agg. Only)

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 7/16/2020

APS00014350 Barriere Construction Co., LLC - Independence, LA**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 7/15/2020

Portland Cement Concrete

APS00014410 Arcosa Aggregates - Pearl River Plant 1725**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 3.3%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/3/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00014780 Cash Sand & Gravel, Inc. - Kemp Plant -D.S., LA****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/5/2021

Portland Cement Concrete

APS00014990**Barriere Construction Co. LLC - Miley Pit****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/22/2022

Portland Cement Concrete

APS00015160**Arcosa Aggregates - Plant LA 1349 - Pearl River****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 3.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

APS00015170**Arcosa Aggregates - Plant LA 1341 - Independence****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

APS00015200**Arcosa Aggregates - Plant LA 1345 - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.49

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00015210 Arcosa Aggregates - Plant LA 1340 - Denham Springs****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

APS00015410 Crawford Aggregate Industries - Cross Pit**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete

APS00015460 Louisiana Aggregate Materials, LLC-Denham Springs**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 2/18/2025

Portland Cement Concrete

APS00015530 Tri-Parish Sand & Gravel, LLC. - Denham Springs**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 2.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 1/5/2026

Portland Cement Concrete

APS00015650 Accardo Mining, LLC. - Bogalusa**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.19

Granular Material for Subbase

Water Absorption = 2.3%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00015670 Candies Excavation, Inc. - Folsom****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 1/12/2024

APS00015680 A-1 Aggregates - KSB Holdings, LLC - Mt. Hermon**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absorption = 2.6%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015750 Community Aggregates, LLC. - Henderson Pit**Material****Approved Uses**

Gravel Only

Base & Surface Course

Spec. Gravity-SSD = 2.47

Granular Material for Subbase

Water Absorption = 2.8%

Asphaltic Surface Treatment

Updated = 6/1/2026

Asphaltic Concrete

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

APS00015890 M & M Gravel - Franklinton**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015980 River Road Materials, LLC. - Franklinton**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

A-1. IN-STATE PRODUCER/SUPPLIERS - BY DISTRICT**District 62****APS00016070 BearCo Construction, LLC. - Franklinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Water Absorption = 4.2%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete

APS00016300 Crawford Aggregate Industries - Lee Brown Pit**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.52

Granular Material for Subbase

Water Absorption = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.60

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00005730 (ASAN) Alabama Sand and Gravel-Prattville, AL****Material****Approved Uses**

Gravel

Base & Surface Course

Billingsley Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.63

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Billingsley Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00005740 (ASAV) Alliance Sand and Gravel, LLC-Phil Campbell, AL**Material****Approved Uses**

Sand Only

Special Embankment (non-plastic)

Phil Campbell Pit

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00005750 (ASAK) Allstate Deatsville, LLC-Deatsville, AL**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Deatsville Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00005780 (ABAO) Arkansas Gravel Company, Inc.-Hampton, AR****Material****Approved Uses**

Gravel

Base & Surface Course

Bradshaw Mine

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Bradshaw Mine

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00005790 (AB76) B & B Gravel & Trucking Co.-Bearden, AR**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.55

Granular Material for Subbase

Water Absorption = 1.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00005830 (ASAR) Baldwin Sand & Gravel-Crystal Springs, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Crystal Springs Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Crystal Springs Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00005920 (ASAM) Blackwell Aggregates, Inc.-Nicholson, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Jackson Landing Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.48

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Jackson Landing Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00005930 (AB31) Blain Sand & Gravel, Inc.-Natchez, MS****Material****Approved Uses**

Gravel

Granular Material for Subbase

Coverhill Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.57

Asphaltic Surface Treatment

Water Absorption = 1.0%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Coverhill Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.62

Water Absorption = 0.5%

Updated = 8/24/2017

APS00005940 (AA57) Blain Sand & Gravel, Inc.-Crystal Springs, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.54

Granular Material for Subbase

Water Absorption = 1.7%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006030 Cossatot Rock, LLC-Lockesburg, AR**Material****Approved Uses**

Gravel

Base & Surface Course

Old Deirks Hwy Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Old Deirks Hwy Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.59

Portland Cement Concrete

Water Absorption = 1.0%

Updated = 8/24/2017

APS00006110 (AA80) Dickerson & Bowen Riverside Gravel-Tylertown, MS**Material****Approved Uses**

Gravel

Base & Surface Course

McComb

Granular Material for Subbase

Spec. Gravity-SSD = 2.46

Special Embankment (non-plastic)

Water Absorption = 4.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

McComb

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006200 (ASAT) Foley Materials Co.-Phenix City, AL- Plant 501****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Plant 501

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

APS00006210 (ASAJ) Foley Materials Co.-Phenix City, AL- Plant 505**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Plant 505

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

APS00006230 (ASAI) Fouke Sand & Gravel, LLC-Fouke, AR**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.61

Granular Material for Subbase

Water Absorption = 0.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006260 (ABAK) Green Brothers Gravel Co.-Hazlehurst, MS**Material****Approved Uses**

Gravel

Base & Surface Course

#22

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 3.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

#22

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006270 (ABAL) Green Brothers Gravel Co.-CrystalSprings, MS**Material****Approved Uses**

Gravel

Base & Surface Course

#65

Granular Material for Subbase

Spec. Gravity-SSD = 2.50

Special Embankment (non-plastic)

Water Absorption = 3.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

#65

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006290 (ASAW) Hallet Materials-Porter,TX****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Porter Plant

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

APS00006300 (ASAU) Hammett Gravel Company, Inc.-Bentonla, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Yazoo City Operation

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absportion = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Yazoo City Operation

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absportion = 0.5%

Updated = 8/24/2017

APS00006310 (AA70) Hanson Aggregates-Bearden,AR**Material****Approved Uses**

Gravel

Base & Surface Course

Eagle Mills

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absportion = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Eagle Mills

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absportion = 0.5%

Updated = 8/24/2017

APS00006320 (A092) Heidelberg Materials - Little River Plant**Material****Approved Uses**

Gravel

Base & Surface Course

Little River F.K.A. Hanson

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absportion = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Little River F.K.A. Hanson

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absportion = 0.5%

Little River F.K.A. Hanson

Updated = 3/12/2025

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006420 (AB07) Huey Stockstill, LLC - Picayune, MS - 12 Oaks****Material****Approved Uses**

Gravel

Base & Surface Course

12 Oaks Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

12 Oaks Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006430 (AB26) Huey P. Stockstill, LLC -Picayune, MS - Pine Grove**Material****Approved Uses**

Gravel

Base & Surface Course

Pine Grove Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Special Embankment (non-plastic)

Water Absorption = 2.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Pine Grove Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006490 (ABAP) JJ Ferguson Sand & Gravel-Cruger, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Blackhawk Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.54

Special Embankment (non-plastic)

Water Absorption = 1.7%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Blackhawk Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/24/2017

APS00006500 (A091) Johnsville Sand & Gravel-Hermitage, AR**Material****Approved Uses**

Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.55

Special Embankment (non-plastic)

Water Absorption = 1.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Spec. Gravity-SSD = 2.62

(Friction Rating = III - Coarse Agg. Only)

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006530 (ASAG) King Sand & Gravel-Kerens, TX****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

APS00006540 (AB91) Krystal Gravel, Inc.-Crystal Springs, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006680 (ASAL) Marion Clay & Gravel, LLC-Columbia, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 3.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006700 (ABAS) Martin Marietta Aggregates-Eagletown, OK**Material****Approved Uses**

Gravel Only

Base & Surface Course

Broken Bow Sand & Gravel

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Asphaltic Surface Treatment

Water Absorption = 1.2%

Asphaltic Concrete

Broken Bow Sand & Gravel

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00006710 (AA92) Martin Marietta Aggregates-Cove,AR**Material****Approved Uses**

Gravel

Base & Surface Course

Traprock

Granular Material for Subbase

Stone

Special Embankment (non-plastic)

(Rhyolite)

Asphaltic Surface Treatment

Traprock

Asphaltic Concrete

Spec. Gravity-SSD = 2.66

(Friction Rating = II - Coarse Agg. Only)

Water Absorption = 0.7%

Portland Cement Concrete

Updated = 7/9/2026

(Stone from this source requires mitigation measures in Portland Cement Concrete mixes, requires 30% Class F fly ash)

Riprap & Stone Revetment

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006720 (ASAX) Martin Marietta Aggregates-Garwood, TX****Material****Approved Uses**

Gravel

Base & Surface Course

Garwood Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.57

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Garwood Plant

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006780 (ABAC) Memphis Stone & Gravel Co.-Nesbit, MS**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Anderson Plant

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

APS00006790 (ABAD) Memphis Stone & Gravel Co.-Senatobia, MS**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Perry Plant

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

APS00006840 (ASAQ) ODDEE Smith Constr.Inc.-Brookhaven, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Oddee California Camp Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Oddee California Camp Pit

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00006860 (A018) Perkinston Sand & Gravel-Perkinston, MS**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006880 (AB13) Pine Bluff Sand & Gravel-Delaware, AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
River Mountain Quarry	Granular Material for Subbase
Sand	Special Embankment (non-plastic)
River Mountain Quarry	Asphaltic Surface Treatment
Stone	Asphaltic Concrete
(Sandstone)	(Friction Rating = I - Coarse Agg. Only)
River Mountain Quarry	Portland Cement Concrete
Spec. Gravity-SSD = 2.63	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
Water Absorption = 1.0%	Riprap & Stone Revetment

Updated = 5/18/2026

APS00006890 (ABBS) Pine Bluff Sand & Gravel-Salem,KY

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Cumberland River Quarry	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Siliceous Limestone)	Asphaltic Surface Treatment
Cumberland River Quarry	Asphaltic Concrete
Spec. Gravity-SSD = 2.68	(Friction Rating = III - Coarse Agg. Only)
Water Absorption = 0.8%	Portland Cement Concrete
Updated = 5/26/2026	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00006910 (ASAF) R & R Logging & Gravel-Columbia, MS

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Spec. Gravity-SSD = 2.49	Granular Material for Subbase
Water Absorption = 3.5%	Special Embankment (non-plastic)
Sand	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	(Friction Rating = III - Coarse Agg. Only)
Updated = 8/24/2017	Portland Cement Concrete

APS00006930 (ASAP) Riverside Sand & Gravel-Tylertown, MS

<u>Material</u>	<u>Approved Uses</u>
Sand Only	Granular Material for Subbase
NW St. Paul Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Concrete
Water Absorption = 0.5%	Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00006980 (ASAY) Simpson Materials Co.-Valley Park, MO****Material****Approved Uses**

Gravel

Base & Surface Course

Ranken Site

Granular Material for Subbase

Spec. Gravity-SSD = 2.51

Special Embankment (non-plastic)

Water Absorption = 2.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Ranken Site

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/28/2017

Portland Cement Concrete

APS00007160 (AB15) Texas Crushed Stone Co., Inc.-Georgetown, TX**Material****Approved Uses**

Gravel

Base & Surface Course

Stone

Granular Material for Subbase

(Limestone)

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.48

Asphaltic Surface Treatment

Water Absorption = 3.6%

Asphaltic Concrete

Updated = 3/12/2025

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(excluding bridge decks)

Riprap & Stone Revetment

APS00007170 (AB27) The Fordyce Co-Victoria, TX**Material****Approved Uses**

Gravel

Base & Surface Course

Briggs Plant

Granular Material for Subbase

Spec. Gravity-SSD = 2.74

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Briggs Plant

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 8/28/2017

APS00007210 (ASAH) Triangle Aggregates, LLC-Jackson, AL**Material****Approved Uses**

Gravel

Base & Surface Course

Couch - Triangle Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.61

Special Embankment (non-plastic)

Water Absorption = 0.8%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Couch - Triangle Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.63

Portland Cement Concrete

Updated = 8/28/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00007250 (ASAE) Trinity Materials-West Lockesburg, AR****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.56

Granular Material for Subbase

Water Absorption = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/28/2017

Portland Cement Concrete

APS00007380 (ABBQ) Vulcan Materials Co-Grand Rivers,KY- Ft Payne**Material****Approved Uses**

Gravel

Base & Surface Course

Ft. Payne Formation

Granular Material for Subbase

Stone

Special Embankment (non-plastic)

(Siliceous Limestone)

Asphaltic Surface Treatment

Ft. Payne Formation

Asphaltic Concrete

Spec. Gravity-SSD = 2.68

(Friction Rating = III - Coarse Agg. Only)

Water Absorption = 0.2%

(Friction Rating = II for ADT <= 20,000 - Coarse Agg. Only)

Updated = 5/26/2026

Portland Cement Concrete

(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00007480 (ABAY) Warren Paving-Salem, KY - Upper Warsaw Formation**Material****Approved Uses**

Gravel

Base & Surface Course

Slats Lucas Quarry

Granular Material for Subbase

Stone

Special Embankment (non-plastic)

(Siliceous Limestone)

Asphaltic Surface Treatment

Slats Lucas Quarry

Asphaltic Concrete

Spec. Gravity-SSD = 2.69

(Friction Rating = III - Coarse Agg. Only)

Water Absorption = 0.4%

(Friction Rating = II for ADT <10,000 - Coarse Agg. Only)

Updated = 7/30/2026

Riprap & Stone Revetment

APS00007510 (ASAA) Wooten Sand & Gravel-Fouke,AR**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.60

Granular Material for Subbase

Water Absorption = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 8/24/2017

Portland Cement Concrete

APS00011350 (ASAS) Eastern Oklahoma Quarries, LLC - Spiro, OK**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spiro Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00011360 (ASAZ) Shale Support Holdings, LLC - Nicholson, MS****Material****Approved Uses**

Gravel

Granular Material for Subbase

Nicholson Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.49

Asphaltic Surface Treatment

Water Absorption = 3.5%

Asphaltic Concrete

Sand

(Friction Rating = III - Coarse Agg. Only)

Nicholson Pit

Portland Cement Concrete

Spec. Gravity-SSD = 2.63

Updated = 8/28/2017

APS00011380 (ASBA) South Gate Aggregates, LLC - Nicholson, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Burge Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 3.5%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Burge Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.63

Portland Cement Concrete

Updated = 8/28/2017

APS00011450 (ASBC) Huey P. Stockstill, LLC- Nicholson, MS**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Santa Rosa Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Updated = 8/24/2017

Portland Cement Concrete

APS00011470 (ASBB) Eastern Oklahoma Quarries - Garland, AR**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Chieftan Sand Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Water Absorption = 0.8%

Portland Cement Concrete

Updated = 8/24/2017

APS00011630 (ASBE) Heidelberg Materials - Bristol Plant**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Bristol Plant F.K.A. Hanson

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.63

Portland Cement Concrete

Updated = 5/22/2023

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00011690 (ASBF) Hammett & Green Aggregates - Vicksburg, MS****Material****Approved Uses**

Gravel

Base & Surface Course

Henry Mine Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.56

Special Embankment (non-plastic)

Water Absorption = 1.2%

Asphaltic Surface Treatment

Sand

Asphaltic Concrete

Henry Mine Pit

(Friction Rating = III - Coarse Agg. Only)

Spec. Gravity-SSD = 2.62

Portland Cement Concrete

Water Absorption = 0.5%

Updated = 1/8/2019

APS00012160**Dickerson & Bowen Co., Inc - Brookhaven, MS****Material****Approved Uses**

Gravel Only

Base & Surface Course

D & B Brookhaven Pit

Granular Material for Subbase

Spec. Gravity-SSD = 2.53

Asphaltic Surface Treatment

Water Absorption = 2.2%

Asphaltic Concrete

Updated = 8/28/2017

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

APS00012380**LeHigh Hanson - Garwood, TX****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Arena Pit

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

Portland Cement Concrete

Updated = 8/24/2017

APS00012890**D & J Construction Company, LLC - West Monroe****Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 1/16/2018

Portland Cement Concrete

APS00012930**Regional Sand & Gravel, LLC #2 - Clinton****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.54

Granular Material for Subbase

Water Absorption = 1.5%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 7/26/2018

Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00012980 Gulf Coast Sand & Gravel - Jackson, AL****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.59

Granular Material for Subbase

Water Absorption = 1.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.63

Asphaltic Concrete

Updated = 1/16/2018

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

APS00013340 Heritage Sand and Gravel - Columbia, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absorption = 3.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 4/7/2020

Portland Cement Concrete

APS00014030 Sierra FRAC Sand - Plain Dealing**Material****Approved Uses**

Sand Only

Granular Material for Subbase

Spec. Gravity-SSD = 2.62

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Concrete

Updated = 11/15/2018

Portland Cement Concrete

APS00014570 Arkansas Granufill Supply - Hot Springs, AR**Material****Approved Uses**

Sand Only

Asphaltic Concrete

Spec. Gravity-SSD = 2.59

Supplemental Fines (screenings) for Asphaltic Concrete

Water Absorption = 1.5%

Updated = 10/5/2021

APS00014750 Rock Island Sand and Gravel - Harrell Pit-Hampton**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.58

Granular Material for Subbase

Water Absorption = 1.0%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 1.0%

(Friction Rating = III - Coarse Agg. Only)

Updated = 10/5/2021

Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00014970 Gulf Coast Sand - Nicholson, MS****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.48

Granular Material for Subbase

Water Absorption = 2.9%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.68

Asphaltic Concrete

Water Absorption = 0.1%

(Friction Rating = III - Coarse Agg. Only)

Updated = 1/27/2022

Portland Cement Concrete

APS00015010 Island Sand & Gravel - Crossett, AR**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.51

Granular Material for Subbase

Water Absorption = 1.8%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.64

Asphaltic Concrete

Water Absorption = 0.2%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015130 Amrize Inc. - Cave-In-Rock, IL - Transition Ledge**Material****Approved Uses**

Gravel

Base & Surface Course

Stone

Granular Material for Subbase

(Limestone)

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.65

Asphaltic Surface Treatment

Water Absorption = 1.3%

Asphaltic Concrete

Updated = 9/29/2025

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

Riprap & Stone Revetment

APS00015180 Arcosa Aggregates - Plant 1347 - Hattiesburg, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/4/2022

Portland Cement Concrete

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS**Out of State****APS00015190 Arcosa Aggregates - Plant 1348 - Columbia, MS****Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.53

Granular Material for Subbase

Water Absorption = 2.2%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.62

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 5/13/2025

Portland Cement Concrete

APS00015540 Hammett Gravel Company, Inc. - Red Mountain Plant**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.50

Granular Material for Subbase

Water Absorption = 3.1%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.64

Asphaltic Concrete

Water Absorption = 0.5%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete

APS00015780 RockCo Mining, LLC. - Courtland, MS**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.54

Granular Material for Subbase

Water Absorption = 1.6%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.65

Asphaltic Concrete

Water Absorption = 0.4%

(Friction Rating = III - Coarse Agg. Only)

Updated = 6/17/2026

Portland Cement Concrete

APS00015900 Huey P. Stockstill, LLC. - Boone Mine**Material****Approved Uses**

Gravel

Base & Surface Course

Spec. Gravity-SSD = 2.45

Granular Material for Subbase

Water Absorption = 3.6%

Special Embankment (non-plastic)

Sand

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.64

Asphaltic Concrete

Water Absorption = 0.1%

(Friction Rating = III - Coarse Agg. Only)

Updated = 3/12/2025

Portland Cement Concrete

APS00016400 West Side Complex - Hayes Quarry**Material****Approved Uses**

Gravel

Base & Surface Course

Sand

Granular Material for Subbase

Stone

Special Embankment (non-plastic)

(Limestone)

Asphaltic Surface Treatment

Spec. Gravity-SSD = 2.52

Asphaltic Concrete

Water Absorption = 3.2%

(Friction Rating = IV - Coarse Agg. Only)

Updated = 10/3/2025

Riprap & Stone Revetment

Bedding Material

A-2. OUT-OF-STATE PRODUCERS/SUPPLIERS

Out of State

APS00016790 Custom Abrasives, LLC.

Material	Approved Uses
Sand Only	Granular Material for Subbase
Spec. Gravity-SSD = 2.61	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 7/21/2026	Portland Cement Concrete

NOTES:

Note A-1:
Source approval samples of gravel and sand are obtained by personnel of the Materials and District Laboratories. The source is defined as the pit or quarry which produces the aggregate being evaluated. All aggregate which does not pass through the 4.75mm (No. 4) sieve shall be source approved prior to use. Certain aggregates may be approved for restricted use. A complete source approval analysis shall be run on each aggregate source.

Note A-2:
All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

Note A-3:
A specific gravity value of 2.62 (SSD) may be used for all in-state silica sands used for portland cement concrete.

Note A-4:
Because absorption has been found to correlate with the type and specific gravity of silica sands and chert gravels, the water absorption factors given in the following table may be used:

B. OTHER AGGREGATE MATERIALS**Out of State****APS00005710 (ABBC) Agrecasa Del Caribe-San Pedro Sula, HON****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.63	Special Embankment (non-plastic)
Water Absorption = 1.6%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00005770 (ABBY) APAC - Brickey's Stone-Bloomsdale, MO - Burlington**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Burlington Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absorption = 1.4%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00005900 (AB25) Arcosa Lightweight - Erwinville, LA**Material****Approved Uses**

Lightweight Aggregate	Special Embankment (non-plastic)
(Expanded Clay)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 1.65	(Type B, C, & D applications only)
Water Absorption = 16.3%	Asphaltic Concrete
Updated = 12/8/2021	(excluding wearing surfaces)
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete

APS00005960 (ABBU) Arcosa Aggregates - Grand Rivers,KY-StLouis**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
St. Louis Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.69	Asphaltic Surface Treatment
Water Absorption = 0.5%	Asphaltic Concrete
Updated = 10/20/2021	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00005970 (ABBK) Texas Materials - Burnet.TX****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
F.K.A OldCastle Materials -	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 5/28/2026	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00006080 (ABBN) Crystal Hill Quarry-North Little Rock, AR**Material****Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Granite Mountain Quarries	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 9/24/2024	(Friction Rating = II - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00006250 (A033) Granite Mountain Quarries-Little Rock, AR**Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Syenite Granite	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.59	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = II - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006340 (A077) Hanson Aggregates-Perch Hill Plant-Chico,TX**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Perch Hill Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00006370 (AA90) Hastie Mining Company-Cave-in-Rock,IL****Material****Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Hastie Mining Company Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 8/24/2017	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006440 (AA91) Ideal Domicana, SA-Santo Domingo, DR**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.61	Special Embankment (non-plastic)
Water Absorption = 1.3%	Asphaltic Surface Treatment
Updated = 8/25/2017	Portland Cement Concrete

APS00006480 (ABBO) Amrize Inc. - Jamaica Aggregates Limited**Material****Approved Uses**

Stone	Base & Surface Course
(Crushed Alluvial Stone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.72	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006560 (ABAN) Amrize Inc. - Cave-In-Rock, IL - SandStone**Material****Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 0.8%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00006570 (ABAM) Amrize Inc. - Cave-In-Rock, IL - Sil. Limestn**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Ledge 8 - 10	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00006580 (ABCA) Amrize Inc. - Fredonia, KY

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00006690 (AA86) Martin Marietta Aggregates-Bahamas,BAH

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Porous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absorption = 3.9%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00006710 (AA92) Martin Marietta Aggregates-Cove,AR**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Traprock	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Rhyolite)	Asphaltic Surface Treatment
Traprock	Asphaltic Concrete
Spec. Gravity-SSD = 2.66	(Friction Rating = II - Coarse Agg. Only)
Water Absorption = 0.7%	Portland Cement Concrete
Updated = 7/9/2026	(Stone from this source requires mitigation measures in Portland Cement Concrete mixes, requires 30% Class F fly ash)
	Riprap & Stone Revetment

APS00006730 (ABAW) Martin Marietta Aggregates-Malvern, AR - SandStone

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Jones Mill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.2%	Asphaltic Concrete
Updated = 8/25/2017	(Friction Rating = II - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

Out of State**APS00006740 (ABAX) Martin Marietta Aggregates-Malvern, AR - Granite**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Jones Mill Pit	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.58	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00006750 (AA39) Martin Marietta Aggregates-Mulgrave, NS

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absorption = 0.9%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(excluding OGFC and coarse mix)
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00006760 (AA51) Martin Marietta Aggregates-Sawyer,OK

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.52	Special Embankment (non-plastic)
Water Absorption = 2.3%	Asphaltic Surface Treatment
Updated = 6/3/2020	Asphaltic Concrete
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires 30% Class F fly ash or 50% slag to mitigate)
	Riprap & Stone Revetment

Out of State

APS00006880 (AB13) Pine Bluff Sand & Gravel-Delaware, AR

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
River Mountain Quarry	Granular Material for Subbase
Sand	Special Embankment (non-plastic)
River Mountain Quarry	Asphaltic Surface Treatment
Stone	Asphaltic Concrete
(Sandstone)	(Friction Rating = I - Coarse Agg. Only)
River Mountain Quarry	Portland Cement Concrete
Spec. Gravity-SSD = 2.63	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
Water Absorption = 1.0%	Riprap & Stone Revetment
Updated = 5/18/2026	

APS00006890 (ABBS) Pine Bluff Sand & Gravel-Salem,KY

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Cumberland River Quarry	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Siliceous Limestone)	Asphaltic Surface Treatment
Cumberland River Quarry	Asphaltic Concrete
Spec. Gravity-SSD = 2.68	(Friction Rating = III - Coarse Agg. Only)
Water Absorption = 0.8%	Portland Cement Concrete
Updated = 5/26/2026	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00007160 (AB15) Texas Crushed Stone Co., Inc.-Georgetown, TX****Material****Approved Uses**

Gravel

Base & Surface Course

Stone

Granular Material for Subbase

(Limestone)

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.48

Asphaltic Surface Treatment

Water Absorption = 3.6%

Asphaltic Concrete

Updated = 3/12/2025

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(excluding bridge decks)

Riprap & Stone Revetment

APS00007180 (A056) Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn8**Material****Approved Uses**

Stone

Base & Surface Course

(Limestone)

Granular Material for Subbase

Spec. Gravity-SSD = 2.64

Special Embankment (non-plastic)

Water Absorption = 1.6%

Asphaltic Surface Treatment

Updated = 5/21/2018

Asphaltic Concrete

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00007190 (A079) Tower Rock Stone Co-St.Genevieve, MO- Oolitic**Material****Approved Uses**

Stone

Base & Surface Course

(Oolitic Stone)

Granular Material for Subbase

Spec. Gravity-SSD = 2.47

Special Embankment (non-plastic)

Water Absorption = 4.8%

Asphaltic Surface Treatment

Updated = 8/25/2017

Asphaltic Concrete

(Friction Rating = III - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

Out of State**APS00007260 (AB61) Martin Marietta - Bridgeport TX****Material****Approved Uses**

Stone

Base & Surface Course

(Limestone)

Granular Material for Subbase

Bridgeport

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.64

Asphaltic Surface Treatment

Water Absorption = 1.3%

Asphaltic Concrete

Updated = 6/24/2022

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(may be used on bridge decks)

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00007340 (A042) Vulcan Materials Co-Calera, AL****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Calera Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.71	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00007350 (AA95) Vulcan Materials Co-Cancun, MEX**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.38	Special Embankment (non-plastic)
Water Absorption = 3.7%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00007380 (ABBQ) Vulcan Materials Co-Grand Rivers,KY- Ft Payne**Material****Approved Uses**

Gravel	Base & Surface Course
Ft. Payne Formation	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Siliceous Limestone)	Asphaltic Surface Treatment
Ft. Payne Formation	Asphaltic Concrete
Spec. Gravity-SSD = 2.68	(Friction Rating = III - Coarse Agg. Only)
Water Absorption = 0.2%	(Friction Rating = II for ADT <= 20,000 - Coarse Agg. Only)
Updated = 5/26/2026	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

APS00007390 (ABBP) Vulcan Materials Co-Grand Rivers,KY- Warsaw**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 0.9%	Asphaltic Concrete
Updated = 10/29/2021	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00007430 (ABBT) Vulcan Materials Co-Tuscumbia, AL- Pride Quarry**

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.60	Special Embankment (non-plastic)
Water Absorption = 1.9%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00007450 (AB19) Vulcan Materials Co-Trinity, AL

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Trinity Plant	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.2%	Asphaltic Concrete
Updated = 10/25/2017	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

Out of State**APS00007480 (ABAY) Warren Paving-Salem, KY - Upper Warsaw Formation**

<u>Material</u>	<u>Approved Uses</u>
Gravel	Base & Surface Course
Slats Lucas Quarry	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Siliceous Limestone)	Asphaltic Surface Treatment
Slats Lucas Quarry	Asphaltic Concrete
Spec. Gravity-SSD = 2.69	(Friction Rating = III - Coarse Agg. Only)
Water Absorption = 0.4%	(Friction Rating = II for ADT <10,000 - Coarse Agg. Only)
Updated = 7/30/2026	Riprap & Stone Revetment

APS00007500 (AB78) Winn Materials, Inc.-Clarksville, TN

<u>Material</u>	<u>Approved Uses</u>
Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.70	Special Embankment (non-plastic)
Water Absorption = 0.6%	Asphaltic Surface Treatment
Updated = 10/28/2021	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00007520 (AB04) Capital Aggregates - Delta Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.56	Special Embankment (non-plastic)
Water Absorption = 2.1%	Asphaltic Surface Treatment
Updated = 8/25/2017	Asphaltic Concrete
	(Friction Rating = I - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00011430 (ABCD) APAC - Brickey's Stone-Bloomsdale, MO - Platin**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Platin Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.60	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 7/26/2018	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

Out of State**APS00011620 (ABCI) Central Stone Co - Farmington, MO****Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Butler Hill Granite Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absorption = 0.3%	Asphaltic Concrete
Updated = 2/16/2024	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00011870 Amrize Inc. - Smithland, KY-Three Rivers-S1**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
3RvrQry-Bench S1-Pit#1	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Updated = 5/20/2020	(Friction Rating = III - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00012130 Tower Rock Stone Co-St.Genevieve, MO- Limestn Zn12****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Ledge 12	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 11/9/2018	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

Out of State**APS00012300 Vulcan Materials Co-West Loachapoka, AL****Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 0.4%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(excluding bridge decks)
	Riprap & Stone Revetment

APS00012320 Arcosa Aggregates - Grand Rivers,KY-Warsaw**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.1%	Asphaltic Concrete
Updated = 11/10/2020	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00012600 Martin Marietta - MMR - Hondo, TX**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Medina Rock & Rail Quarry	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 2.2%	Asphaltic Concrete
Updated = 8/29/2017	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00012680 Warren Paving-Salem, KY-Lower High Calcium Ledge****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Lower Warsaw Formation	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/24/2022	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00012880 Amrize Inc. - Smithland, KY-Three Rivers-S2**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absorption = 0.8%	Asphaltic Surface Treatment
Updated = 5/20/2020	Asphaltic Concrete
	(excluding OGFC and coarse mix)
	(Friction Rating = III - Coarse Agg. Only)
	Riprap & Stone Revetment

Out of State**APS00012960 APAC R4 Obrus S.A. D.C.V. - Boca Del Rio, Mexico****Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.89	Special Embankment (non-plastic)
Water Absorption = 1.5%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00013370 Canteras LA Ponderosa S.A. - OoliticStnFormtn -5.1**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.71	Special Embankment (non-plastic)
Water Absorption = 1.2%	Asphaltic Surface Treatment
Updated = 2/21/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00014110****Rogers Group - Lacey's Springs Quarry****Material****Approved Uses**

Stone

Base & Surface Course

(Limestone)

Granular Material for Subbase

Spec. Gravity-SSD = 2.70

Special Embankment (non-plastic)

Water Absorption = 0.7%

Asphaltic Surface Treatment

Updated = 2/14/2020

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014340**Amrize Inc. - Smithland, KY-Upper Fredonia****Material****Approved Uses**

Stone

Base & Surface Course

(Siliceous Limestone)

Granular Material for Subbase

Spec. Gravity-SSD = 2.70

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Updated = 10/21/2020

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Riprap & Stone Revetment

Out of State**APS00014530****Martin Marietta - Mill Creek - Granite****Material****Approved Uses**

Stone

Base & Surface Course

(Granite)

Granular Material for Subbase

Spec. Gravity-SSD = 2.74

Special Embankment (non-plastic)

Water Absorption = 1.0%

Asphaltic Surface Treatment

Updated = 2/16/2024

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014540**Martin Marietta - Mill Creek - Limestone****Material****Approved Uses**

Stone

Base & Surface Course

(Dolomitic Limestone)

Granular Material for Subbase

Spec. Gravity-SSD = 2.81

Special Embankment (non-plastic)

Water Absorption = 0.4%

Asphaltic Surface Treatment

Updated = 5/31/2022

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00014560****Shorline Aggregates Inc. - South Brook Quarry****Material****Approved Uses**

Stone

Base & Surface Course

(Granite)

Granular Material for Subbase

Spec. Gravity-SSD = 2.71

Special Embankment (non-plastic)

Water Absorption = 0.5%

Asphaltic Surface Treatment

Updated = 2/16/2024

Asphaltic Concrete

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

Riprap & Stone Revetment

APS00014700**Heidelberg Materials-Servtex Quarry-New Braunfels****Material****Approved Uses**

Stone

Base & Surface Course

(Limestone)

Granular Material for Subbase

F.K.A. Hanson Aggregates

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.57

Asphaltic Surface Treatment

Water Absorption = 2.0%

Asphaltic Concrete

Updated = 5/22/2023

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)

(excluding bridge decks)

Riprap & Stone Revetment

APS00014710**Arcosa Lightweight - Livingston, AL****Material****Approved Uses**

Lightweight Aggregate

Special Embankment (non-plastic)

(Expanded Clay)

Asphaltic Surface Treatment

Spec. Gravity-SSD = 1.07

Asphaltic Concrete

Water Absorption = 20.8%

(Friction Rating = I - Coarse Agg. Only)

Updated = 12/8/2021

Portland Cement Concrete

Out of State**APS00014740****Heidelberg Materials - Burnet Quarry****Material****Approved Uses**

Stone

Base & Surface Course

(Siliceous Limestone)

Granular Material for Subbase

F.K.A. Hanson Aggregates -

Special Embankment (non-plastic)

Spec. Gravity-SSD = 2.78

Asphaltic Surface Treatment

Water Absorption = 0.6%

Asphaltic Concrete

Updated = 5/22/2023

(Friction Rating = IV - Coarse Agg. Only)

Portland Cement Concrete

(excluding bridge decks)

Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**APS00014900****Southern Stone Company - Neely's Landing Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.62	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 10/20/2021	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

Out of State**APS00014980****Arcosa Lightweight - Streetman Plant****Material****Approved Uses**

Lightweight Aggregate	Asphaltic Surface Treatment
(Expanded Shale)	Asphaltic Concrete
Spec. Gravity-SSD = 1.65	(Friction Rating = I - Coarse Agg. Only)
Water Absorption = 14.1%	Portland Cement Concrete

Updated = 12/2/2022

APS00015020**APAC Brickey Stone - Bloomdale - Kimmswick****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 1.3%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015110**Amrize Inc. - Cave-In-Rock, IL-Dolomite Ledge****Material****Approved Uses**

Stone	Base & Surface Course
(Dolomitic Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 1.1%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00015120 Amrize Inc. - Cave-In-Rock, IL-Upper St. Gen Ledge****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 0.9%	Asphaltic Surface Treatment
Updated = 6/24/2022	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015130 Amrize Inc. - Cave-In-Rock, IL - Transition Ledge**Material****Approved Uses**

Gravel	Base & Surface Course
Stone	Granular Material for Subbase
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.3%	Asphaltic Concrete
Updated = 9/29/2025	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00015230 Shoreline Agg., Inc. - Point Rousse Quarry**Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.79	Special Embankment (non-plastic)
Water Absorption = 0.4%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(Friction Rating = III - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00015310 Hastie Mining and Trucking #2 - Cave-In-Rock, IL**Material****Approved Uses**

Stone	Base & Surface Course
(Siliceous Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.69	Special Embankment (non-plastic)
Water Absorption = 1.0%	Asphaltic Surface Treatment
Updated = 6/13/2025	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00015390 Matco Aggregates LLC. - Actopan Quarry - Basalt****Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Granular Material for Subbase
Spec. Gravity-SSD = 2.87	Special Embankment (non-plastic)
Water Absorption = 2.1%	Asphaltic Surface Treatment
Updated = 2/16/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00015610 CEMEX 4200 Balcones Quarry - New Braunfels, TX**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.58	Special Embankment (non-plastic)
Water Absorption = 1.5%	Asphaltic Surface Treatment
Updated = 8/12/2025	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015630 Amrize Inc. - Cave-In-Rock, IL - Downeys Bluff Led**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.67	Asphaltic Surface Treatment
Water Absorption = 1.1%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00015640 Coastal Industrial Resources, LLC-Gibralgar Quarry**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 1.6%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00015720 GCA Materials - May Pen, Jamaica****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.65	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 9/15/2023	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00015790 Cemex Materials Newfoundland, Inc. - Canada**Material****Approved Uses**

Stone	Base & Surface Course
(Dolomitic Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.75	Asphaltic Surface Treatment
Water Absorption = 0.4%	Asphaltic Concrete
Updated = 11/13/2023	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00015840 Souter Limestone and Minerals, LLC. - Gore, OK**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Granular Material for Subbase
Spec. Gravity-SSD = 2.67	Special Embankment (non-plastic)
Water Absorption = 0.7%	Asphaltic Surface Treatment
Updated = 1/12/2024	Asphaltic Concrete
	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(may be used on bridge decks)
	Riprap & Stone Revetment

APS00015850 Amrize, Inc.-Three Rivers Quarry -Smithland, KY S3**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absorption = 1.0%	Asphaltic Concrete
Updated = 1/29/2024	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00015940 Two Countries Materials S.A. DE CV - Mexico**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 2.0%	Asphaltic Concrete
Updated = 3/14/2024	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00016010 Tajo Chirripo S.A. - Limon****Material****Approved Uses**

Stone	Base & Surface Course
(Basalt Rock)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.66	Asphaltic Surface Treatment
Water Absorption = 1.6%	Asphaltic Concrete
Updated = 3/18/2026	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	Riprap & Stone Revetment

APS00016120 Antoine Rock Quarry - Delight, AR**Material****Approved Uses**

Stone	Riprap & Stone Revetment
(Limestone)	
Updated = 9/10/2024	

Out of State**APS00016400 West Side Complex - Hayes Quarry****Material****Approved Uses**

Gravel	Base & Surface Course
Sand	Granular Material for Subbase
Stone	Special Embankment (non-plastic)
(Limestone)	Asphaltic Surface Treatment
Spec. Gravity-SSD = 2.52	Asphaltic Concrete
Water Absorption = 3.2%	(Friction Rating = IV - Coarse Agg. Only)
Updated = 10/3/2025	Riprap & Stone Revetment
	Bedding Material

APS00016410 Southland Resources, Inc.**Material****Approved Uses**

Stone	Base & Surface Course
(Sandstone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.62	Asphaltic Surface Treatment
Water Absorption = 1.9%	Riprap & Stone Revetment
Updated = 7/24/2025	

APS00016440 Amrize Agg.-Smithland Three Rivers-Middle Fredonia**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absorption = 1.7%	Riprap & Stone Revetment
Updated = 10/3/2025	

B. OTHER AGGREGATE MATERIALS**Out of State****APS00016450 Eiffage Infraestructuras SA - Cartagena Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absorption = 0.8%	Asphaltic Concrete
Updated = 12/10/2025	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00016470 Eiffage Infraestructuras SA - La Algueña Quarry**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.6%	Asphaltic Concrete
Updated = 12/11/2025	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00016510 New Frontier Materials - Barnhart Quarry Ledges 10**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.64	Asphaltic Surface Treatment
Water Absorption = 1.9%	Asphaltic Concrete
Updated = 3/25/2026	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00016520 New Frontier Materials - Barnhart Quarry Ledges 1F**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.53	Asphaltic Surface Treatment
Water Absorption = 3.6%	Asphaltic Concrete
Updated = 3/25/2026	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00016560 Cemex Materials Newfoundland, Inc. - Canada - Dolo**Material****Approved Uses**

Stone	Base & Surface Course
(Dolomitic Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.78	Asphaltic Surface Treatment
Water Absorption = 0.6%	Asphaltic Concrete
Updated = 6/9/2026	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source is potentially deleterious in Portland Cement Concrete mixes, requires mitigation by 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

B. OTHER AGGREGATE MATERIALS**Out of State****APS00016670 Industrias Bisoño SRL - La Borda Quarry****Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.45	Asphaltic Surface Treatment
Water Absorption = 2.7%	Asphaltic Concrete
Updated = 5/13/2026	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

APS00016680 Carver Materials Canada LTD**Material****Approved Uses**

Stone	Base & Surface Course
(Granite)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.68	Asphaltic Surface Treatment
Water Absorption = 0.6%	Asphaltic Concrete
Updated = 8/11/2026	(Friction Rating = IV - Coarse Agg. Only)
	Portland Cement Concrete
	(Stone from this source requires mitigation measures in Portland Cement Concrete mixes, requires 30% Class F fly ash, 50% slag, or ternary blend of Class F fly ash and GGBFS with a minimum of 50% replacement)
	Riprap & Stone Revetment

APS00016700 Eiffage Infraestructuras SA - Vélez Quarry**Material****Approved Uses**

Stone	Base & Surface Course
(Limestone)	Special Embankment (non-plastic)
Spec. Gravity-SSD = 2.82	Asphaltic Surface Treatment
Water Absorption = 0.7%	Asphaltic Concrete
Updated = 6/17/2026	(Friction Rating = IV - Coarse Agg. Only)
	Riprap & Stone Revetment

NOTES:**Note B-1:**

Refer to Subsections 501.02 and 1003.06 for definition and application of Friction Ratings.

Note B-2:

All material, regardless of prior approval, shall be sampled in accordance with the Materials Sampling Manual and tested for conformance to the appropriate specifications. Any deviation in performance from the original sample submitted may result in removal of the material from the approved list.

REFERENCE:

DOTD Standard Specifications and Special Provisions, Section 1003
 DOTD Supplemental Specifications
 DOTD Maintenance Specifications

No information contained in this list is to be used for promotional purposes.